



## Product Data Sheet

### PRODUCT DESCRIPTION

7025-01 is a transparent modified alkyd sealer for use on chalky or previously painted surfaces, uncoated cured concrete and stucco substrates. It bonds and adheres tightly, providing a firm base for application of Neoflex and other waterborne architectural grade latex coatings. Aids in reducing moisture penetration, increases coverage of finish coat and is alkali-resistant.

### PRODUCT NUMBERS AND COLORS

Standard Color: 7025-01 Translucent White

### PRODUCT DATA

Description	Test Method	Results
Weight/Gal	ASTM D1475	10.2 lbs/gal
Weight Solids	ASTM D4209	61%
Volume Solids	Calculated	55%
VOC	EPA Method 24	348 g/L
Viscosity	ASTM D2196	100 cps
Flash Point	ASTM D3278	112°F
Adhesion	ASTM D4541	>100 psi
Dry Time @ 75°F & 50% RH	ASTM D5895	4 hrs, Tack-free 8 hrs, Through dry

The above tested results are typical values. Individual lots may vary up to 10% from the typical value.

### SURFACE PREPARATION

Surfaces should be clean, dry and structurally sound. Remove all chipped or peeling paint and coating.

### APPLICATION INSTRUCTIONS

Apply at a rate of 500 square feet per gallon. Application will vary depending upon surface and conditions. May be applied by brush, roller or spray application.

### HEALTH AND SAFETY

Read the Material Safety Data Sheet (MSDS) and container labels for detailed health and safety information. This product is intended for use by properly trained professional applicators only.

The information, data and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyer's process. **SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED** as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of any product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of, the NEOGARD® Division of JONES-BLAIR®. 100107/7025-01PD.indd

**NEOGARD®**

Div. of JONES-BLAIR®

2728 Empire Central - P.O. Box 35286 - Dallas, Texas 75235 - Toll Free (800) 321-6588 - Fax (214) 357-7532 - www.neogard.com