

NEOGARD® Quick Notes

Pot Life and Time to Recoat with Accelerators



Date: March 15, 2011
From: Technical Department

70613 - Applied 16 Wet Mils Thick

Accelerator	Amount	Potlife			Time to Recoat		
		40°F, 60%RH	75°F, 50%RH	95°F, 50%RH	40°F, 60%RH	75°F, 50%RH	95°F, 50%RH
none	none	> 7 days	> 7 days	> 7 days	48 hrs	14 hrs	11 hrs
7930	8 oz	>24 hrs	>24 hrs	>24 hrs	22 hrs	10 hrs	8 hrs
7930	16 oz	>24 hrs	>24 hrs	>24 hrs	20 hrs	8 hrs	6 hrs
7931	16 oz	>24 hrs	>24 hrs	12 hrs	18 hrs	6 hrs	6 hrs
7923	8 oz	>24 hrs	12 hrs	8 hrs	20 hrs	8 hrs	7 hrs
7923	16 oz	11 hrs	4 hrs	2.5 hrs	13 hrs	7 hrs	5 hrs

Manufacturer warrants that the standards and qualities of the product described herein will not vary by more than 10% from the tested results set forth above. **MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.** Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. **To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS.** Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. 03152010/70613PTRChart.indd

NEOGARD Div. of JONES-BLAIR

2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com