



### Product Data Sheet

#### PRODUCT DESCRIPTION

NEOCRETE SL (70800/70801/70804) is a water dispersed polyurethane resin combined with powder for use as a resurfacing system. Formulated to provide excellent resistance to abrasion, impact and chemical attack. Provides excellent performance against thermal shock stresses such as hot water and daily steam cleaning. Highly resistant to acids, caustics, fuels, oils, and solvents. U.S.D.A. acceptable. Mix 90 fluid ounces of 70800 with 63 fluid ounces of 70801 and one bag of 70804 powder.

#### PRODUCT NUMBERS AND COLORS

Standard colors:

- 70800-02 (Color Resin) ..... Gray
- 70800-05 (Color Resin) ..... Red
- 70801 (Hardener)
- 70804 (Powder)

#### CURED RESIN PERFORMANCE

Description	Test Method	Results
Compressive Strength	ASTM C579	7,700 psi
Tensile Strength	ASTM C307	712 psi
Flexural Strength	ASTM C580	2,200 psi
Modulus of Elasticity	ASTM C580	446,700 psi
Shore D Hardness	ASTM D2240	84
Adhesion (concrete)	ASTM D4541	400 psi
Water Resistance	ASTM C413	0.42%
Density	ASTM C905-01	121 lbs/ft <sup>3</sup>
Coefficient of Thermal Expansion	ASTM C531	2.4 x 10 <sup>-5</sup> in/in/°F
Resistance to Fungal Growth	ASTM G21	No Support of Growth
Flammability	ASTM D635	Pass

The above tested results are typical values. Individual lots may vary up to 10% from the typical value.

#### PRODUCT DATA

Description	Test Method	Results
Weight Solids (mixed)	ASTM D5201	99.95%
Volume Solids (mixed)	ASTM D5201	99.93%
Flash Point	ASTM D3278	None
VOC (mixed)	ASTM D5201	8.4 g/L
Shelf Life		1 year
Usable Pot Life @ 70°F		15 minutes
Initial Join Up Time @ 70°F per 1/8"		20 minutes
Cure to Foot Traffic @ 70°F per 1/8"		4 - 8 hours
Cure to Full Use @ 70°F per 1/8"		10 - 16 hours
Application Temperature Range		34°F to 90°F
Temperature Range		-120°F to 210°F
Typical Thickness		1/8"
Mixed Unit Coverage @ 1/8"		30 square feet

The above tested results are typical values. Individual lots may vary up to 10% from the typical value.

#### APPLICATION

NEOCRETE SL (70800/70801/70804) can be applied to the following substrates: concrete, polymer reinforced screeds, properly supported wood floors, etc.

It is applied with a gauge rake or notched squeegee in a one-step system and requires no primers or sealers. To be assured of maximum adhesion, correct surface preparation is essential.

Regular cleaning of applied surface is recommended in order to maintain slip resistance and aesthetics.

For surface preparation and application instructions, refer to NEOGARD's Flooring Application Manual for specific applications.

#### HEALTH AND SAFETY

Read the Material Safety Data Sheet (MSDS) and container labels for detailed health and safety information. This product is intended for use by properly trained professional applicators only.

Manufacturer warrants that the standards and qualities of the product described herein will not vary by more than 10% from the tested results set forth above. **MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.** Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. **To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS.** Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. 12012010/70800-70801-70804PD.indd

NEOGARD Div. of JONES-BLAIR

2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com