



### Product Data Sheet

#### PRODUCT DESCRIPTION

70861/70865 is a low odor, fast set, high solids, two-component semi-gloss aliphatic polyurea that exhibits excellent UV stability and quick cure characteristics that will allow foot traffic in as little as three hours.

Designed to be used as a semi-gloss topcoat for any NEO-GARD® decorative flooring system where UV resistance is desired.

#### FEATURES

- Quick cure
- Semi-gloss
- Abrasion resistant
- UV resistant
- Very durable, excellent weatherability

#### PRODUCT NUMBERS AND COLORS

70860 - Semi-clear/Colorless      70865 - Clear/Colorless

#### CURED FILM PERFORMANCE

Description	Test Method	Results
Tensile Strength	ASTM D412	3,500 psi
Elongation	ASTM D412	90%
Permanent Set	ASTM D412	20%
Water Resistance	ASTM D471	1.6%
MVT @ 12 mils	ASTM E96	0.23 Perm
Taber Abrasion	ASTM D4060	40 mg/1,000 rev cs17
Shore A	ASTM D2240	95
Shore D	ASTM D2240	54
Flammability	ASTM D635	Pass
Adhesion to...	ASTM D4541	500 psi - Concrete 500 psi - 7760/7761 600 psi - 7779/7781 500 psi - 70714/70715 600 psi - 70734/70735 500 psi - 70860/70865 500 psi - 7430 500 psi - FC7520/FC7962 500 psi - FC7530/FC7963

The above tested results are typical values. Individual lots may vary up to 10% from the typical value.

#### PRODUCT DATA

Description	Test Method	Results
Mix Ratio		1:1 (vol) with 70865
Weight/Gal (mixed)	ASTM D1475	8.5 lbs/gal
Weight Solids (mixed)	ASTM D4209	76%
Volume Solids (mixed)	Calculated	72%
VOC (mixed)	EPA Method 24	249 g/L
Viscosity (mixed)	ASTM D2196	110 cps
Flash Point	ASTM D3278	115°F
Coefficient of Friction	ASTM F1679	0.75 dry 0.42 wet
Pot Life @ 75°F, 50% RH		1 hr
Dry to Touch		1/2 hr
Dry to Walk-on		3 hrs
Shelf Life		1 year

The above tested results are typical values. Individual lots may vary up to 10% from the typical value.

#### DIRECTIONS FOR USE

THINNING: Do not thin.

MIXING: Read container labels, MSDS and application instructions prior to mixing. Mix 55 gallon drums and 5 gallon pails with a variable speed drill utilizing a jiffy mixer to suspend any settled pigment and attain a uniform color. Time will vary depending on temperature conditions.

APPLICATION: Mix thoroughly before application. May be applied by brush, roller or airless spray equipment.

#### HANDLING & STORAGE

Keep containers tightly closed. Store in protected area. Ideal storage temperature range for ease of handling is 50°F to 85°F.

#### HEALTH AND SAFETY

Read the Material Safety Data Sheet (MSDS) and container labels for detailed health and safety information. This product is intended for industrial use by properly trained professional applicators only.

Manufacturer warrants that the standards and qualities of the product described herein will not vary by more than 10% from the tested results set forth above. **MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.** Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. **To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS.** Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. 12152010/70861-70865PD.indd

#### NEOGARD Div. of JONES-BLAIR

2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com