



Product Data Sheet

PRODUCT DESCRIPTION

7261 is a high solids, fire retardant, quick-set elastomeric acrylic coating for application over polyurethane foam, concrete, wood, metal, masonry and other types of properly prepared surfaces. This coating is not designed for use on roofs that have any ponding water.

PRODUCT NUMBER AND COLOR

Standard color is: White

CURED RESIN PERFORMANCE

Description	Test Method	Results
Tensile Strength	ASTM D2370	280 psi
Elongation	ASTM D2370	270%
Permanent Set	ASTM D412	<20%
Water Resistance	ASTM D471	<20%
MVT @ 30 mils	ASTM E96	2.9 English
Adhesion	ASTM D903	5 lb/in

PRODUCT DATA

Description	Test Method	Results
Weight/Gal	ASTM D1475	11.5 lbs/gal
Weight Solids	ASTM D4209	63%
Volume Solids	Calculated	50%
VOC	EPA Method 24	38 g/L
Viscosity	ASTM D562	105 KU
Flash Point	ASTM D3278	None
Red Label		No
Pot Life		N/A
Shelf Life		2 years (unopened container)
Cure Time @ 75°F, 50% RH		1 - 2 hrs

LIMITATIONS AND PRECAUTIONS

Do not apply 7261 at temperatures below 50°F, or when there is a possibility of temperatures falling below 32°F within a 12 hour period after application.

7261 requires complete evaporation of water to cure. Cool temperatures and high humidity retard cure. Do not apply if weather conditions will not permit complete cure before rain, dew, or freezing temperatures occur. Do not apply in the late afternoon if heavy condensation may appear during the night.

THINNING AND CLEANUP

Thinning of materials is not required under normal application conditions. However, if required, thin material with water. Never thin more than 10% without consulting NEOGARD®.

Water should be used for cleaning equipment.

STORAGE

Drums and cans of coating material should be stored in a cool (75°F) area.

WARNING!

Protect Material from Freezing.

7261 will freeze and become unusable at temperatures below 32°F.

HEALTH AND SAFETY

Read the Material Safety Data Sheet (MSDS) and container labels for detailed health and safety information. This product is intended for use by properly trained professional applicators only.

Manufacturer warrants that the standards and qualities of the product described herein will not vary by more than 10% from the tested results set forth above. **MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.** Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. **To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS.** Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. 02152011/7261PD.indd

NEOGARD Div. of JONES-BLAIR

2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com