

7430-CA SERIES

Product Data Sheet

PRODUCT DESCRIPTION

7430-CA series is a single component moisture-cured, aromatic polyurethane coating designed for use as a waterproofing membrane for pedestrian and vehicular traffic bearing surfaces and meets South Coast AQMD.

PRODUCT COLOR

Standard colors are: 7430-CA Gray
7435-CA Tan

CURED FILM PERFORMANCE

Description	Test Method	Results
Tensile Strength	ASTM D412	2,500 psi
Elongation	ASTM D412	400%
Permanent Set	ASTM D412	<30%
Tear Resistance	ADTM D1004	200 lb/in
Water Resistance	ASTM D471	<3%
MVT @ 30 Mils	ASTM E96	1.3 English
Taber Abrasion	ASTM D4060	25 mg/1,000 cs-17
Shore A	ASTM D2240	75 - 80
Adhesion	ASTM D4541	300 psi

PRODUCT DATA

Description	Test Method	Results
Weight/Gal	ASTM D1475	10.7 lbs/gal
Weight Solids	ASTM D4209	80%
Volume Solids	Calculated	76%
VOC	EPA Method 24	97 g/l
Viscosity	ASTM D562	87 KU
Flash Point	ASTM D3278	101°F
Pot Life		8 hrs
Shelf Life		1 year
Cure Time @ 75°F and 50% RH	TT-S-0023OA	24 hrs

APPLICATIONS

7430-CA series is designed for use as a surface applied waterproofing membrane on a variety of prepared substrates.

- Parking Decks
- Mechanical equipment room floors
- Walking decks
- Balconies
- Rooftop recreational areas
- Sun decks
- Lab flooring (Heavy-Duty)
- Clean rooms (Heavy-Duty)
- Animal holding areas (Heavy-Duty)

For surface preparation and application instructions, refer to NEOGARD® Guide Specifications.

SAFETY

This product contains flammable aromatic solvents. Excessive contact with bare skin should be avoided. It is good practice to wear gloves and to guard against splashing the coating or solvent. Inhalation of fumes or vapor should be avoided. Use a NIOSH approved respirator.

Thinning of materials is not required under normal application conditions. However, if required, thin material with VOC exempt solvent. Never thin more than 10% without consulting NEOGARD®.

STORAGE

Every precaution should be taken to prevent fire. Drums and cans of coatings and solvents should be stored in a cool (75°F) area safe from fire exposure. When specified on container, protect materials from freezing. Open containers, the liquid coating, its fumes and vapor must be kept away from any source of ignition, heat, sparks, arcing switches, open flames, including pilot lights, cutting torches and all tools that could cause sparks. Do not smoke. Use explosion proof equipment. Foam or dry powder fire extinguishers should be placed where they can be quickly and safely reached in case of fire.

information, data and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyer's process. **SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED** as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of any product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of, the NEOGARD® Division of JONES-BLAIR™. 022706//7430-CAPD.indd

NEOGARD®
Div. of JONES-BLAIR™

2728 Empire Central - P.O. Box 35286 - Dallas, Texas 75235 - Toll Free (800) 321-6588 - Fax (214) 357-7532 - www.neogard.com

