



Product Data Sheet

PRODUCT DESCRIPTION

7922 is a vertical additive for wide variety of urethane to enhance the sag resistant properties of the coating material.

PRODUCT NUMBER AND COLOR

Standard color is: 7922 Amber

USAGE CHART

7922 can be used for the following urethane coating products with a 30 minute induction time.

Products	7922/5 gals	Sag Resistance (mls)
7401	1/2 pint	16 - 18
7425	2 x 1/2 pints	14 - 16
7430	2 x 1/2 pints	14 - 16
7435	2 x 1/2 pints	14 - 16
7441	2 x 1/2 pints	14 - 16
7442	2 x 1/2 pints	14 - 16
7443	2 x 1/2 pints	14 - 16
7419	1/2 pint	16 - 18
70611	1/2 pint	>50
70612	1/2 pint	>50
70613	1/2 pint	>50
70620	1/2 pint	>50
70405	1/2 pint	12 - 14
70410	1/2 pint	14 - 16

PRODUCT DATA

Description	Test Method	Results
Weight/Gal	ASTM D1475	9.1 lbs/gal
Weight Solids	ASTM D4209	100%
Volume Solids	Calculated	100%
VOC	EPA Method 24	0.0 g/L
Viscosity	ASTM D2196	100 cps
Flash Point	ASTM D3278	250+°F
Pot Life (mixed with urethane coating @ 75°F and 50% RH)	Calculated	90 - 120 minutes
Shelf Life		1 year
Cure Time @ 75°F and 50% RH	TT-S-00230A	24 hrs

The above tested results are typical values. Individual lots may vary up to 10% from the typical value.

HEALTH AND SAFETY

Before using this product, carefully read the Material Safety Data Sheet (MSDS) and container labels for detailed health and safety information. This product is intended for industrial use by properly trained professional applicators only.

Manufacturer warrants that the standards and qualities of the product described herein will not vary by more than 10% from the tested results set forth above. **MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.** Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. **To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS.** Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. 10262010/7922PD.indd

NEOGARD Div. of JONES-BLAIR

2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com