

**CHEMICAL RESISTANT CHART**

Rating Key: 0 - No Effect 1 - Stains/Dulls 2 - Blisters 3 - Lifts Film

<u>Chemical</u>	<u>Rating</u>	<u>Chemical</u>	<u>Rating</u>
Acetic Acid 98%.....	3	Mustard.....	0*
Acetic Acid 36%.....	2	Nitric Acid 30% .....	2
Acetic Acid 20%.....	2	Nitric Acid 10% .....	1
Acetic Acid 10%.....	1	Oleic Acid.....	1-2
Ammonia 28% .....	0	Phenol .....	2
Blood .....	0-1	Phosphoric Acid 25%.....	2
Brake Fluid .....	0-1	Potassium Hydroxide 25% .....	0
Butyl Alcohol.....	1-2	Propylene Glycol .....	0
Butoxyethanol.....	2	Skydrol.....	1
Butoxyethylacetate .....	2	Sodium Hypochloride 10% .....	0
Butylacrylate.....	1	Sodium Hydroxide (50%).....	0
Calcium Chloride 10%.....	0	Sodium Hydroxide (25%).....	0
Chromic Acid 2% .....	1	Solvent 100.....	1
Diacetone Alcohol.....	1	Sulfuric Acid (96%) .....	2
Diesel Fuel .....	0	Sulfuric Acid (50%) .....	1
Ethyl Acetate .....	1	Sulfuric Acid (20%) .....	1
Ethyl Alcohol.....	1	Sulfuric Acid (10%) .....	1
Ethylene Glycol .....	0	Tall Oil Fatty Acid .....	2
Formic Acid 38% .....	2	Urine .....	0*
Gasoline .....	0	Vegetable Oil .....	0
Isopropyl Alcohol .....	1	Vinegar .....	1
Jet Fuel.....	0	Xylene.....	1
Lactic Acid 85% .....	0-1		
Lactic Acid 50% .....	1		
Lactic Acid 20% .....	1		
Hydrobromic 48%.....	1		
Hydrochloric Acid 37% .....	0		
Hydrochloric Acid 15% .....	0		
Hydrochloric Acid 5% .....	0		
Hydrofluoric Acid 48% .....	2		
Hydrofluoric Acid 24% .....	2		
Methylisobutyl Ketone .....	0		
Methylpyrrolidione .....	2		
Mineral Spirits.....	0		
Motor Oil.....	0		

**\*Note: Staining is possible with mustard and urine on white and clear systems.**

The information, data and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyer's process. **SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED** as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of any product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of NEOGARD®, a division of JONES-BLAIR® Company. 09102006/7072470715CRC.indd

**NEOGARD®**  
Div. of JONES-BLAIR®

2728 Empire Central - P.O. Box 35286 - Dallas, Texas 75235 - Toll Free (800) 321-6588 - Fax (214) 357-7532 - www.neogard.com

