

CHEMICAL RESISTANT CHART

Rating Key: 0 - No Effect 1 - Stains/Dulls 2 - Blisters 3 - Lifts Film

<u>Chemical</u>	<u>Rating</u>	<u>Chemical</u>	<u>Rating</u>
Acetic Acid 98%	2-3	Phenol	3
Acetic Acid 33%	0-1	Phosphoric Acid 25%	0
Acetic Acid 28%	0	Potassium Hydroxide 25%	0
Acetic Acid 10%	0	Propylene Glycol	0
Ammonia 28%	0	Skydrol	1-2
ATF	0-1	Sodium Hydroxide 50%	1
Blood	0	Sodium Hydroxide 25%	0
Brake Fluid	1	Sodium Hypochlorite	1
Butyl Alcohol	0	Solvent 100	1
Butoxyethanol	1	Sulfuric Acid 96%	3
Butoxyethylacetate	0	Sulfuric Acid 50%	1-2
Butylacrylate	0	Sulfuric Acid 10%	0
Calcium Chloride	0	Tall Oil Fatty Acid	0
Chromic Acid 2%	0	Urine	0*
Diacetone Alcohol	0	Vegetable Oil	0
Ethyl Acetate	0	Vinegar	0
Ethyl Alcohol	0	Xylene	1
Ethylene Glycol	0		
Formic Acid 38%	3		
Gasoline	0		
Glycolic Acid 70%	0-1		
Heavy Aromatic Solvent	0		
Hydrobromic 48%	1-2		
Hydrochloric Acid 37%	0		
Hydrochloric Acid 15%	0		
Hydrofluoric Acid 48%	3		
Isopropyl Alcohol	0		
Ketchup	0		
Lactic Acid 50%	1		
Lactic Acid 20%	1		
Methylisobutyl Ketone	1		
Motor Oil	0		
Mustard	0*		
Nitric Acid 30%	1		
Oleic Acid	0		

***Note: Staining is possible with mustard and urine on white and clear systems.**

The information, data and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyer's process. **SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED** as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of any product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of NEOGARD®, a division of JONES-BLAIR® Company. 100506/AcrylithaneCCRC.indd

NEOGARD®
Div. of JONES-BLAIR®

2728 Empire Central - P.O. Box 35286 - Dallas, Texas 75235 - Toll Free (800) 321-6588 - Fax (214) 357-7532 - www.neogard.com

