

## CHEMICAL RESISTANT CHART

Rating Key: 0 - No Effect 1 - Stains/Dulls 2 - Blisters 3 - Lifts Film

<u>Chemical</u>	<u>Rating</u>
Acetic Acid 98% .....	2
Acetic Acid 33% .....	0
Acetic Acid 10% .....	0
Ammonia 28% .....	0
ATF .....	0
Blood .....	0
Brake Fluid .....	1
Butyl Alcohol .....	0
Butoxyethylacetate .....	0-1
Butylacrylate .....	0
Calcium Chloride .....	0
Chromic Acid 2% .....	0
Diacetone Alcohol .....	0
Ethyl Acetate .....	1
Ethyl Alcohol .....	0
Ethylene Glycol .....	0
Formic Acid 38% .....	2-3
Gasoline .....	0
Glycolic Acid 70% .....	0
Heavy Aromatic Solvent .....	0
Hydrobromic 48% .....	3
Hydrochloric Acid 37% .....	1
Hydrochloric Acid 15% .....	0
Hydrofluoric Acid 48% .....	2
Isopropyl Alcohol .....	0
Ketchup .....	0
Lactic Acid 50% .....	0-1
Lactic Acid 20% .....	0-1
Methylisobutyl Ketone .....	0
Motor Oil .....	0
Mustard .....	0*
Nitric Acid 30% .....	2
Oleic Acid .....	0
Phenol .....	3
Phosphoric Acid 25% .....	0
Potassium Hydroxide 25% .....	0
Propylene Glycol .....	0
Skydrol .....	1
Sodium Hydroxide 50% .....	0

<u>Chemical</u>	<u>Rating</u>
Sodium Hydroxide 25% .....	0
Sodium Hydroxide 10% .....	0
Sodium Hypochlorite .....	1
Solvent 100 .....	0
Sulfuric Acid 96% .....	2
Sulfuric Acid 50% .....	0
Sulfuric Acid 10% .....	0
Tall Oil Fatty Acid .....	0
Urine .....	0*
Vegetable Oil .....	0
Vinegar .....	0
Xylene .....	0

**\*Note: Staining is possible with mustard and urine on white and clear systems.**

The information, data and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyer's process. **SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED** as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of any product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of NEOGARD®, a division of JONES-BLAIR® Company. 09102006/AcrylithaneHS3CRC.indd

