

CHEMICAL RESISTANT CHART

Rating Key: 0 - No Effect 1 - Stains/Dulls 2 - Swells 3 - Blisters/Lifts Film
 Ratings are based on 7-day spot test

<u>Chemical</u>	<u>Rating</u>
Ammonia, 28%	0
Bleach	1
Brake Fluid	2
Calcium Chloride, 10%.....	0
Ethylene Glycol	0
Hydrochloric Acid, 15%	1
Hydrochloric Acid, 5%	1
Isopropyl Alcohol	1
Jet Fuel	0
Gasoline	0
Mineral Spirits	0
Motor Oil.....	0
Nitric Acid, 5%	1
Oleic Acid	1
Phosphoric Acid, 10%	1
Propylene Glycol	0
Sodium Hypochlorite, 10%.....	1
Sodium Hydroxide, 50%.....	1
Sodium Hydroxide, 20%.....	1
Soya Oil.....	1
Sulfuric Acid, 20%	1
Sulfuric Acid, 10%	1
Sulfuric Acid, 5%	1
Tall Oil Fatty Acid.....	2
Transmission Oil.....	1

The information, data and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyer's process. **SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED** as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of any product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of NEOGARD®, a division of JONES-BLAIR® Company. 04142010/FC7540CRC.indd

