

**Guide Specification****PART 1 GENERAL****1.1 SUMMARY**

- A. Provide labor, materials, equipment and supervision necessary to install a minimum 1/8" nominal thickness superior chemical resistant flooring system as outlined in this specification.
- B. The manufacturers application instructions for each product used are considered part of this specification and should be followed at all times.
- C. Related Sections:
 1. Section 03 30 00 - Cast-in-Place Concrete
 2. Section 07 92 00 - Joint Sealants
 3. Section 07 95 00 - Expansion Control

1.2 SYSTEM DESCRIPTION

- A. Novolac Superior Chemical Resistant Epoxy Mortar shall be a complete system of compatible materials supplied by NEOGARD® to create a heavy duty flooring system utilizing silica quartz aggregate to provide an aesthetic, superior chemical resistance, good thermal shock resistance and durable wearing surface.
- B. Novolac Superior Chemical Resistant Epoxy Mortar shall be designated for application on the specific type of substrate indicated on the drawings.

1.3 SUBMITTALS

- A. Product Data: Submit NEOGARD® product literature and installation instructions.
- B. Project Reference List: Submit list of projects as required by this specification.
- C. Samples: Submit samples of specified broadcast and trowel flooring system. Samples shall be construed as examples of finish only.
- D. Applicator Approval: Submit letter from manufacturer stating applicator is approved to install the superior chemical resistant epoxy mortar flooring system.
- E. Warranty: Submit copy of manufacturers standard warranty.

1.4 QUALITY ASSURANCE

- A. Supplier Qualifications: Novolac Superior Chemical

Resistant Epoxy Mortar, as supplied by NEOGARD®, is approved for use on this project.

- B. Applicator Qualifications: Applicators shall be approved to install specified system.

1.5 DELIVERY, STORAGE AND HANDLING

- A. Delivery: Materials shall be delivered in original sealed containers, clearly marked with supplier's name, brand name and type of material.
- B. Storage and Handling: Recommended material storage temperature is 75°F (23.8°C). Handle products to avoid damage to container. Do not store for long periods in direct sunlight.

1.6 PROJECT CONDITIONS

- A. Environmental Conditions:
 1. Do not proceed with application of materials when substrate temperature is less than 50°F (10°C). It is recommended to maintain a minimum concrete temperature of 50°F (10°C) for a minimum of 48 hours before, during and after installation, or until cured.
 2. Concrete must be free of hydrostatic, capillary or moisture vapor pressure. Substrates in contact with ground must have a properly installed, effective vapor barrier to help prevent potential problems resulting from hydrostatic, capillary or moisture vapor pressure. Moisture content of concrete not to exceed four pounds per 1,000 square feet per 24 hours when tested by the referee or quantitative calcium chloride test method.
 3. Do not apply materials unless surface to receive coating is clean and dry.

1.7 WARRANTY

- A. Upon request, NEOGARD® shall offer the manufacturer's standard warranty upon receipt of a properly executed warranty request form.

PART 2 PRODUCTS**2.1 MANUFACTURER**

- A. NEOGARD® Division of JONES-BLAIR® Company, P.O. Box 35286, Dallas, TX 75235, Toll Free (800) 321-6588, Fax (214) 357-7532, www.neogard.com.

2.2 MATERIALS

- A. Novolac Superior Chemical Resistant Epoxy Mortar:
 1. Crack and Joint Filler: 70718/70719 flexible epoxy.
 2. Fillers: P1934 fumed silica and 86364 blended aggregates.
 3. Primer: 70714/70715 clear epoxy.
 4. Novolac Epoxy: 70704/70705 pigmented epoxy.
 5. Aggregate: Silica quartz 86364 blended aggregate.

6. Sealant: 70991 or other polyurethane sealant approved by NEOGARD®.

2.3 MATERIAL PERFORMANCE CRITERIA

- A. Typical performance requirements of cured 70704/70705 novolac epoxy used on this project are:

PERFORMANCE REQUIREMENTS OF CURED FILM		
PHYSICAL PROPERTIES	TEST METHOD	RESULTS
Compressive Strength	ASTM D695	10,000 psi
Tensile Strength	ASTM D638	8,500 psi
Elongation	ASTM D638	6%
Flexural Strength	ASTM D790	11,800 psi
Flexural Modulus	ASTM D790	134,000 psi
Shore D Hardness	ASTM D2280	84
Adhesion	ASTM D4541	300 psi
Taber Abrasion (cs17)	ASTM D4060	40 mg/1,000 rev
Water Resistance	ASTM D570	0.15%
MVT @ 10 mils	ASTM E96	0.15 Perm
Flame Spread	ASTM D2843	Class "A"
Smoke Density Rating	ASTM D2843	36.3%

- B. Typical performance requirements of cured 70704/70705 troweled epoxy mortar used on this project are:

PERFORMANCE REQUIREMENTS OF CURED FILM		
PHYSICAL PROPERTIES	TEST METHOD	RESULTS
Compressive Strength	ASTM C579	4,600 psi
Tensile Strength	ASTM C307	1,800 psi
Flexural Strength	ASTM C580	2,900 psi
Modulus of Elasticity	ASTM C580	0.832x10 ⁶ psi
Heat Resistance	MIL-D-3234F	Pass
Impacted Load	ASTM D6905	Pass @ ≤104 lbs

2.4 MIXES

- A. Comply with manufacturer's instructions for mixing procedures.
- B. Carefully measure and mix the components together.

PART 3 EXECUTION

3.1 EXAMINATION

- A. Verify that the work done under other sections meets the following requirements:
1. That the concrete substrate surface is free of ridges and sharp projections, sound and dry.
 2. That the concrete was cured for a minimum of 28 days (minimum of 3,500 psi compressive strength). The use of concrete curing agents, if any, shall be of a sodium silicate base only; others require written approval from NEOGARD®.
 3. That damaged areas of the concrete substrate be restored to match adjacent areas. Use 70714/70715 epoxy and oven-dry silica aggregate approved by NEOGARD® for filling and leveling at a ratio of one part epoxy mixed with four parts aggregate by volume.

3.2 PREPARATION

- A. Protection:
1. Protect adjacent surfaces from damage resulting from work of this trade. If necessary, mask and/or cover adjacent surfaces, fixtures, equipment, etc. by suitable means.
 2. Provide a suitable work station to mix the coating materials.
- B. Surface Preparation:
1. Cleaning: Surfaces contaminated with oil or grease shall be vigorously scrubbed with a power broom and a strong, non-sudsing detergent. Thoroughly wash, clean and dry. Areas where oil or other contaminants penetrate deep into the concrete may require removal by mechanical methods.
 2. Steel shotblast the surface to remove surface contaminants. Proper care and procedure should be taken to leave the concrete surface as unopened as possible. An improper steel shotblast can cause "pinholes" in concrete surfaces, which can result in blister problems during the application of the superior chemical resistant flooring system. Note: Shotblasting does not remove deep penetrating oils, grease, tar or asphalt stains. Proper cleaning procedures should be followed to insure proper bonding of the epoxy flooring.
 3. Non-moving Cracks: After shotblasting, fill all non-moving cracks with 70714/70715 epoxy mixed with P1934 fumed silica to form a paste. The mix ratio is one part 70714/70715 epoxy to 2 (up to 3) parts P1934 fumed silica by volume.
 4. Moving Cracks or Control Joints: Route all large cracks, remove dust and debris, and fill flush with 70718/70719 flexible epoxy.
 5. Moving Control Joints: Seal secondary control joints with 70991 sealant. Re-incorporate expansion joints and control joints into flooring system if conditions require. Consult NEOGARD® for details on moving cracks, expansion joint details and moving control joints.
 6. Surface Condition: Concrete must be free of hydrostatic, capillary or moisture vapor pressure. Substrates in contact with ground must have a properly installed, effective vapor barrier to help prevent potential problems resulting from hydrostatic, capillary or moisture vapor pressure. Moisture content of concrete not to exceed four pounds per 1,000 square feet per 24 hours when tested by the referee or quantitative calcium chloride test method.
 7. Do not apply materials unless surface to receive coating is clean and dry.

3.3 APPLICATION

- A. BROADCAST METHOD
1. First Base Coat: Mix 70714/70715 clear epoxy at a ratio of 2:1 by volume for three minutes. Apply at a minimum rate of 80 square feet per gallon (20 mils DFT) to prepared substrate with a notched squeegee or notched trowel. Back roll with a short napped phenolic roller to assure even coverage.

2. Aggregate: Broadcast blended 86364 silica quartz into wet epoxy base coat until refusal at a rate of approximately 50 pounds per 100 square feet. Maintain a one to two foot wet edge without any aggregate to allow for a smooth transition to the next pass of neat epoxy. Allow to cure 8 to 12 hours @ 70°F (21.1°C). Remove excess aggregate and lightly sand with a circular floor sander and #50 grit sandpaper to remove any rough spots.
3. Second Base Coat: Mix 70704/70705 pigmented novolac epoxy at a ratio of 3:2 by volume for three minutes. Apply at a rate of 80 square feet per gallon (20 mils DFT) to prepared substrate with a notched squeegee or notched trowel. Back roll with a short napped phenolic roller to assure even coverage.
4. Aggregate: Broadcast blended 86364 silica quartz into wet epoxy base coat until refusal at a rate of approximately 50 pounds per 100 square feet. Maintain a one to two foot wet edge without any aggregate to allow for a smooth transition to the next pass of neat epoxy. Allow to cure 8 to 12 hours @ 70°F (21.1°C). Remove excess aggregate and lightly sand with a circular floor sander and #50 grit sandpaper to remove any rough spots.
5. Steps 3.3A3 and 3.3A4 achieve a nominal thickness of 1/16". Repeat steps 3.3A3 and 3.3A4 until required thickness is achieved. The minimum thickness for a broadcast system should be 1/8".
6. First Seal Coat: Mix 70704/70705 pigmented novolac epoxy at a ratio of 3:2 for three minutes. Apply first seal coat of 70704/70705 at a rate of 200 square feet per gallon (8 mils DFT). Allow to cure 24 hours @ 70°F (21.1°C) before allowing foot traffic.
7. Second Seal Coat: Mix 70704/70705 novolac pigmented epoxy at a ratio of 3:2 for three minutes. Apply second seal coat of 70704/70705 at a rate of 200 square feet per gallon (8 mils DFT). Allow to cure 24 hours @ 70°F (21.1°C) before allowing foot traffic.
8. Optional Topcoat: To maximize chemical resistance and ease of maintenance, please consult NEOGARD® flooring technical department for finish coat.

B. TROWEL METHOD

1. Primer: Mix 70714/70715 clear epoxy at a ratio of 2:1 for three minutes. Apply at a minimum rate of 200 square feet per gallon (8 mils DFT). Immediately lightly broadcast 86364 blended aggregates into wet primer to create an anchor profile for the trowel grade material. Primer should be tack free before applying trowel grade material.
2. Trowel Grade: Mix 70704/70705 pigmented epoxy at a ratio of 3:2 for three minutes. Add approved aggregate blend at a ratio of 4:1 by volume to resin binder. Screed, rake or trowel mix to required thick-

ness. Smooth and tightly close surface with a power or hand trowel. Lightly mist mineral spirits as a trowel lubricant to help smooth and finish the trowel grade surface, and allow to cure 8 to 12 hours @ 70°F (21.1°C). Lightly sand with a circular floor sander to help smooth any rough areas or trowel marks.

3. Grout Coat: Mix 70704/70705 pigmented novolac epoxy at a ratio of 3:2 for three minutes. Apply grout coat of 70704/70705 pigmented novolac epoxy at a rate of 200 square feet per gallon (8 mils DFT) and allow to cure 10 to 14 hours @ 70°F (21.1°C) or until tack free.
4. First Seal Coat: Mix 70704/70705 pigmented novolac epoxy at a ratio of 3:2 for three minutes. Apply first seal coat of 70704/70705 pigmented novolac epoxy at a rate of 200 square feet per gallon (8 mils DFT) and allow to cure 10 to 14 hours @ 70°F (21.1°C) or until tack free.
5. Second Seal Coat: Mix 70704/70705 pigmented novolac epoxy at a ratio of 3:2 for three minutes. Apply second seal coat of 70704/70705 pigmented novolac epoxy at a rate of 200 square feet per gallon (8 mils WFT). Allow to cure 24 hours @ 70°F (21.1°C) before allowing foot traffic.
6. Optional Topcoat: To maximize chemical resistance and ease of maintenance, please consult NEOGARD® flooring technical department for finish coat.

3.4 CLEANING

- A. Remove debris resulting from completion of coating operation from the project site.
- B. Reference Seamless Flooring Systems Manual for typical cleaning methods.

3.5 PROTECTION

- A. After completion of application, do not allow heavy traffic on coated surfaces for a period of at least 48 hours at 75°F (23.8°C), or until completely cured 7 days @ 70°F (21.1°C).

END OF SECTION

The information, data, and suggestions herein are believed to be reliable, based on Manufacturer's knowledge and experience. However, Manufacturer does not guarantee the result to be obtained in the Buyer's process. With regard to those products described herein that are manufactured by Manufacturer, Manufacturer warrants that the standards and qualities of such products will not vary by more than 10% from the tested results set forth in the Product Data Sheets associated with such products. **MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.** Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. **To the extent any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO ANY OF MANUFACTURER'S PRODUCTS.** Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. NovolacBroadcastTrowel CSI.indd

NEOGARD Div. of JONES-BLAIR

2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com