

**Guide Specification****PART 1 GENERAL****1.1 SUMMARY**

- A. Furnish all labor, materials, tools and equipment necessary to install a cold fluid-applied waterproofing membrane suitable to be overlaid with thin-set tile to new or existing concrete surfaces as specified in this section.
- B. The manufacturer's application instructions for each product used are considered part of this specification and should be followed at all times.
- C. Related Sections:
  1. Section 03 30 00 - Cast-in-Place Concrete
  2. Section 07 90 00 - Joint Protection

**1.2 SYSTEM DESCRIPTION**

- A. PEDA-GARD® TS shall be a complete system of compatible materials supplied by NEOGARD® to create a seamless waterproof membrane.
- B. PEDA-GARD® TS shall be designated for application on the specific type of deck indicated on the drawings.

**1.3 SUBMITTALS**

- A. Product Data: Submit manufacturers' product data, material safety data sheets (MSDS) and installation instructions for the thin-set tile cold fluid-applied waterproofing system.
- B. Project Reference List: Submit list of projects as required by this specification.
- C. Samples: Submit samples of specified thin-set tile cold fluid-applied waterproofing system. Samples shall be construed as examples of finished color and texture of the system only.
- D. Applicator Approval: Submit letter from manufacturer stating applicator is approved to install the thin-set tile cold fluid-applied waterproofing system.
- E. Warranty: Submit copy of manufacturer's standard warranty.

**1.4 QUALITY ASSURANCE**

- A. Supplier Qualifications: PEDA-GARD® TS, as supplied by NEOGARD®, is approved for use on this project.
- B. Applicator Qualifications: Applicators shall be approved to install specified system.
- C. Requirement of Regulatory Agencies: Materials used in the thin-set tile cold fluid-applied waterproofing system shall meet existing Federal, State and local VOC regulations.

**1.5 DELIVERY, STORAGE AND HANDLING**

- A. Delivery: Materials shall be delivered in original sealed containers, clearly marked with supplier's name, brand name and type of material.
- B. Storage and Handling: It is recommended to store materials at 75°F (23°C) with careful handling to prevent damage to products. All materials shall be stored in compliance with local fire and safety requirements. Do not store at high temperature or in direct sunlight.

**1.6 JOB CONDITIONS**

- A. Environmental Conditions:
  1. Do not proceed with application of materials when deck temperature is less than 40°F (4.4°C).
  2. Do not apply materials unless surface to receive coating is clean and dry, or if precipitation is imminent.

**1.7 WARRANTY**

- A. Upon request, NEOGARD® shall offer its standard warranty upon receipt of a properly executed warranty request form.

**PART 2 PRODUCTS****2.1 MANUFACTURER**

- A. NEOGARD® Division of Jones-Blair® Company, P.O. Box 35286, Dallas, TX 75235, Toll Free (800) 321-6588 Fax (214) 357-7532, www.neogard.com.

**2.2 MATERIALS**

- A. PEDA-GARD® TS:
  1. Primer: Concrete and metal primers as required by NEOGARD®.

2. Flashing Tape: 86218 flashing tape (ETERNA-BOND™ WebSeal™) or approved equal having a minimum thickness of 30 mils.
3. Liquid Flashing: 7400 series polyurethane coating.
4. Base Coat/Wearing Surface: 7400 series polyurethane coating, gray or tan in color.
5. Aggregate: 7992 silica (quartz) sand or other aggregate approved by NEOGARD®.
6. Sealant: 70991 or other polyurethane sealant approved by NEOGARD®.

### 2.3 MATERIAL PERFORMANCE CRITERIA

- A. Typical performance requirements of cured thin-set tile cold fluid-applied waterproofing system used on this project are:

PERFORMANCE REQUIREMENTS OF CURED FILM		
PHYSICAL PROPERTIES	TEST METHOD	RESULTS
Tensile Strength	ASTM D412	2,500 psi
Elongation	ASTM D412	400%
Permanent Set	ASTM D412	<30%
Tear Resistance	ASTM D1004	200 pli
Water Resistance	ASTM D471	<3% @ 7 days
MVT @ 20 mils	ASTM E96	1.3 English
Taber Abrasion (cs17)	ASTM D4060	25 mg/1,000 rev
Shore A	ASTM D2240	75 - 80
Adhesion	ASTM D4541	300 psi
"Standard Specifications for High-Solids Content, Cold-Applied Elastomeric Waterproofing Membrane with Integral Wearing Surface"	ASTM C957	System Exceeds Requirements

### 2.4 ACCESSORIES

- A. Thin-set tile adhesives, setting materials and grouts, not covered in this specification, shall be recommended by the manufacturer of these materials.
- B. Miscellaneous materials such as cleaning agents, adhesives, backer rod, deck drains, etc. shall be a composite part of the deck system and shall be compatible with the specified thin-set tile cold fluid-applied waterproofing system.

## PART 3 - EXECUTION

### 3.1 EXAMINATION

- A. Concrete: Verify that the work done under other sections meets the following requirements:
1. That the concrete deck surface is free of ridges and sharp projections. If metal forms or decks are used they should be ventilated to permit adequate drying of concrete on exterior exposed deck.
  2. That the concrete was cured for a minimum of 28 days. (Minimum of 3,000 psi compressive strength).

Water-cured treatment of concrete is preferred. The use of concrete curing agents, if any, shall be of the sodium silicate base only; others require written approval by NEOGARD®.

3. That the concrete was finished by a power or hand steel trowel followed by soft hair broom to obtain light texture or "sidewalk" finish.
4. That damaged areas of the concrete deck be restored to match adjacent areas. Use 100% solids epoxy and sand for filling and leveling.

### 3.2 PREPARATION

- A. Protection:
1. Mask off all adjoining areas that are not to receive the thin-set tile cold fluid-applied waterproofing system.
  2. Provide a suitable work station to mix the coating materials.
- B. Surface Preparation:
1. Cleaning: Surfaces contaminated with oil or grease shall be vigorously scrubbed with a power broom and a strong non-sudsing detergent. Thoroughly wash, clean, and dry. Areas where oil or other contaminants penetrate deep into the concrete may require removal by mechanical methods.
  2. Shot Blasting: Required surface preparation method for remedial construction, is also the preferred method for new construction. Mechanically prepare surface by shot blasting to industry standard surface texture (ICRI's CSP3-4) without causing additional surface defects in deck surface. Shot blasting does not remove deep penetrating oils, grease, tar or asphalt stains. Proper cleaning procedures should be followed to insure proper bonding of the deck coating. Note: If shot blasting is not practical, treat concrete surfaces with 10% to 15% solution of muriatic acid to remove laitance and impurities. After acid has stopped foaming or boiling, immediately rinse thoroughly with water. Re-rinse as required to remove muriatic acid solution. Acid etching does not remove deep penetrating oils, grease, tar or asphalt stains. Proper cleaning procedures should be followed to insure proper bonding of the deck coating.
  3. Cracks and Cold Joints: Visible hairline cracks (up to 1/16" in width) in concrete and cold joints shall be cleaned, primed as required and treated with liquid flashing a minimum distance of 2" on each side of crack to yield a total thickness of 30 dry mils. Large cracks (over 1/16" in width) shall be routed and sealed with 70991 sealant. Sealant shall be applied to inside area of crack only, not applied to deck surface. Detail sealed cracks with liquid flashing a distance of 2" on each side of crack to yield a total thickness of 30 dry mils.
  4. Control Joints: Seal secondary control joints with

70991 sealant. Sealant shall be applied to inside area of joint only, not applied to deck surface. Detail sealed joints with liquid flashing a distance of 2" on each side of joint to yield a total thickness of 30 dry mils.

5. Flashing Tape: Install flashing tape where indicated on the drawings prior to the application of the thin-set tile cold fluid-applied waterproofing.
6. Surface Condition: Surface shall be clean and dry prior to coating.

### 3.3 APPLICATION

- A. Primer: Where required, apply 1/3 gallon per 100 square feet (300 sf/gal) to all concrete surfaces in strict accordance with procedures outlined by NEOGARD®. Within 24 hours of application of primer, base coat must be applied. If base coat cannot be applied within 24 hours, reprime.
- B. Base Coat: Apply 2-1/2 gallons per 100 square feet (80 sf/gal) of 7400 series polyurethane coating material in a minimum of two coats to deck surfaces in strict accordance with procedures outlined by NEOGARD®. Extend base coat over cracks and control joints which have received treatment.

- C. Wearing Surface Coat: Apply 1/2 gallon per 100 square feet (200 sf/gal) of 7400 series polyurethane coating material in strict accordance with procedures outlined by NEOGARD® and immediately broadcast aggregate, evenly distributed, into wet coating at the rate of 10 pounds per 100 square feet or until solidly textured. When dry, remove excess aggregate. Total system thickness averages 36 dry mils exclusive of aggregate.

\*Note to specification writer: Thickness can vary due to finish of surface.

### 3.4 CLEANING

- A. Remove debris resulting from completion of coating operation from the project site.

### 3.5 PROTECTION

- A. After completion of application, do not install thin-set tile for at least 24 hours at 75°F (23°C) and 50% R.H., or until thin-set tile cold fluid-applied waterproofing system is completely cured.

END OF SECTION

---

The information, data and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyer's process. **SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED** as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of any product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of, the NEOGARD® Division of JONES-BLAIR®. PedaGardTSGS CSI.indd

**NEOGARD®**  
Div. of JONES-BLAIR®

2728 Empire Central - P.O. Box 35286 - Dallas, Texas 75235 - Toll Free (800) 321-6588 - Fax (214) 357-7532 - www.neogard.com