## **Product Data Sheet**

# 7475 (47MJB) Integrally Textured Aliphatic Urethane



**Description:** 7475 series (Hempel 47MJB) is an integrally textured, single-component, aliphatic urethane.

**Recommended use:** As a weather protective topcoat the Neogard Auto-Gard T vehicular traffic-bearing waterproofing

system.

**Availability:** Available in North America. Not included in Group Assortment; other regions must confirm.

#### Colors and packaging:

7475-002 (47MJB16650) Gray 7475-003 (47MJB23820) Tan

7475-003 (47M3B23620) Fall 5-gallon pails 7475-041 (47MJB16680) Charcoal Gray

7475-058 (47MJB61300) Dark Maple

Some standard colors and/or packaging may have extended lead times and/or minimum quantities. Contact

Neogard for additional colors.

#### **Physical constants:**

Tensile strength 2,500 psi ASTM D412 250% ASTM D412 Elongation Permanent set <20% ASTM D412 Tear resistance 400 pli **ASTM D1004** Water resistance 1%, 7 days ASTM D471 MVT at 20 mils 2.5 English Perm ASTM E96 10 mg/1,000 CS-17 Taber abrasion **ASTM D4060** Shore A 88-92 **ASTM D2240** Adhesion >400 psi **ASTM D4541** 

Weight/gallon 9.74 lbs/gal **ASTM D1475 ASTM D4209** Weight solids 85.9% at 12 hours Volume solids Calculated 81.2% VOC 163.4 g/L EPA Method 24 Viscosity KU **ASTM D2196** Flash point 110°F/43°C By Comparison

Shelf life 1 year

SRI value: 7470-011 82 ASTM E1980-01

Cure to recoat at 75°F/23°C, 8–12 hours, 72 hours for

50% relative humidity vehicular traffic

The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further

technical information can be found at www.neogard.com.

#### **Application details:**

Application method: Squeegee or roller (do not dip and roll from container)

Thinner (max.vol.): Hempel's Thinner 08080 (xylene) (10%)

Mixing: Mix for 3–5 minutes before applying; Jiffy Mixer paddle recommended

Cleaning of tools: Hempel's Thinner 08080 (xylene)

Safety: Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels

on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or

national safety regulations.

**Application conditions:** Substrate temperature must be between 40°F/4°C and 110°F/32°C.

**Preceding coat:** According to Neogard Guide Specifications.

Issued: July 2021 Page: 1/2

## **Product Data Sheet**

### 7475 (47MJB) **Integrally Textured Aliphatic Urethane**



Accelerators and additives: 7986 (994JB00000): Odor mask, synthetic vanilla scent.

7923 (9505300000): Accelerator for single component urethanes.

7931 (9905500000): Fast accelerator for use in low humidity environments.

Store in a cool area to ensure full shelf life. Recommended temperature: 75°F/23°C. Storage temperature:

Remarks: Not recommended for constant immersion. Do not apply over asphaltic compounds. For on-grade

applications, substrates constructed over unvented metal decks or between-slab applications,

contact Neogard Technical Service.

Note: 7475 is for professional use only.

Hempel (USA) - 47MJB Issued by:

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to update from time-to-time. Accordingly, the buyer/applicator should refer to the PDS current as of the time of delivery. In addition to the PDS, the buyer/applicator may receive some or all of the specifications, statements and/or guidelines listed below or available at www.neogard.com (the "Additional Documents"):

**Document Description** No

**PDS** 

- **Guide Specification** 2
- 3 Application Manual
- 4 Other Technical Support Information (i.e. summary application tables, troubleshooting guides, maintenance manuals, chemical resistance charts and other

In the event of a conflict between this PDS and the Additional Documents, the conflict shall be resolved in accordance with the order of priority set forth above. In addition, the buyer/applicator should refer to the relevant Safety Data Sheet current as of the time of delivery and available at www.neogard.com. Buyer/applicator is responsible for determining the suitability of the intended use of the Product, and Neogard disclaims all responsibility for any use, handling and storage of the Product that is not in accordance with the requirements set forth in the relevant PDS and the Additional Documents. The terms and provisions hereof apply to this PDS, the Additional Documents and any other documents supplied by Neogard in respect of the Product. The Product is supplied and all technical assistance is given subject to the General Conditions of Sale of Hempel Products and/or Services available at www.hempel.com. NEOGARD MAKES NO OTHER WARRANTY THAT EXTENDS BEYOND THE WARRANTY REFERENCED THEREIN INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTIES OR CONDITIONS OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. NEOGARD WILL NOT BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR BREACH OF ANY EXPRESS OR IMPLIED WARRANTY OR CONDITION, OR THAT IN ANY WAY ARISE IN RELATION TO THE PRODUCT. 7475-PDS ksk 07092021 docx

Neogard®, a part of Hempel 2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com

Issued: July 2021 Page: 2/2