

# Product Data Sheet

## 600 FTS (960JB) MMA Flooring BPO Initiator



<b>Description:</b>	600 FTS (Hempel 960JB) is a fine, granular powder.
<b>Recommended use:</b>	600 FTS is used as an initiator/curing agent for Neogard FTS MMA floor coating products.
<b>Features:</b>	Easy to handle Easy dispersion in MMA (methyl methacrylate) liquids Dissolves quickly
<b>Availability:</b>	Available in North America. Not included in Group Assortment. Availability subject to confirmation.

### Colors and packaging:

600 FTS (960JB00000P010)	White	10-lb box
600 FTS (960JB00000P055)	White	55-lb box

### Physical constants:

Assay	49.0%–51.0%
Water	2.5% maximum

*The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at [www.neogard.com](http://www.neogard.com).*

### Application details:

<b>Mixing:</b>	Jiffy Mixer preferred. Mix with 100 FTS, 101 FTS, 200 FTS, 250 FTS, 300 FTS, 301 FTS or 400 FTS for 60 seconds or until completely mixed. Note: Extended mixing time will shorten working time of the material.
<b>Dosage rate:</b>	Refer to the dosage chart below for correct dosage. Dosage rates change based upon ambient air temperature.
<b>Safety:</b>	Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations.
<b>Storage:</b>	Store at or below 77°F/25°C. Protect against direct sunlight.

# Product Data Sheet

## 600 FTS (960JB) MMA Flooring BPO Initiator



Resin Type	32°F-44°F	45°F-59°F	60°F-74°F	75°F-89°F	90°F-98°F
FTS F100 Primer (104 volume oz.) FTS F101 Adhesion Promotor (24 volume oz.)	8.0 - 7.0	6.5 - 5.5	5.0 - 4.0	4.0 - 3.0	2.0
FTS F200 Flex Resin	9.5 - 8.5	8.0 - 7.5	7.0 - 6.0	5.5 - 4.5	4.0
FTS F250 Membrane	18.0 - 13.0	13.0 - 6.0	6.0 - 3.0	3.0 - 1.5	1.5
FTS F300 Body Resin	6.5 - 6.0	5.0 - 4.0	3.5 - 3.0	2.5 - 2.0	1.5
FTS F301 Cove Resin	6.5 - 6.0	5.0 - 4.0	3.5 - 3.0	2.5 - 2.0	1.5
FTS F302 Flake Cove Broadcast	6.5 - 6.0	5.0 - 4.0	3.5 - 3.0	2.5 - 2.0	1.5
FTS F400 Topcoat	5.5 - 4.5	4.0 - 3.0	2.5 - 2.0	1.5	1.5
FTS 450 Topcoat	6.5 - 5.0	5.0 - 3.5	3.5 - 2.5	2.5 - 2.0	2.0 - 1.5
<b>Amount of Powder Hardener (BPO) per 1.75 Gallon Batch of Self-Leveling Slurry</b>					
FTS F300 Body Resin	11.5 - 10.5	8.75 - 7.00	6.25 - 5.25	4.5 - 3.5	2.75

Note: **600 FTS is for professional use only.**

Issued by: Hempel (USA) – 960JB

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to update from time-to-time. Accordingly, the buyer/applicator should refer to the PDS current as of the time of delivery. In addition to the PDS, the buyer/applicator may receive some or all of the specifications, statements and/or guidelines listed below or available at [www.neogard.com](http://www.neogard.com) (the "Additional Documents"):

No.	Document Description
1	PDS
2	Guide Specification
3	Application Manual
4	Other Technical Support Information (i.e. summary application tables, troubleshooting guides, maintenance manuals, chemical resistance charts and other technical information)

In the event of a conflict between this PDS and the Additional Documents, the conflict shall be resolved in accordance with the order of priority set forth above. In addition, the buyer/applicator should refer to the relevant Safety Data Sheet current as of the time of delivery and available at [www.neogard.com](http://www.neogard.com). Buyer/applicator is responsible for determining the suitability of the intended use of the Product, and Neogard disclaims all responsibility for any use, handling and storage of the Product that is not in accordance with the requirements set forth in the relevant PDS and the Additional Documents. The terms and provisions hereof apply to this PDS, the Additional Documents and any other documents supplied by Neogard in respect of the Product. The Product is supplied and all technical assistance is given subject to the General Conditions of Sale of Hempel Products and/or Services available at [www.hempel.com](http://www.hempel.com). NEOGARD MAKES NO OTHER WARRANTY THAT EXTENDS BEYOND THE WARRANTY REFERENCED THEREIN INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTIES OR CONDITIONS OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. NEOGARD WILL NOT BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR BREACH OF ANY EXPRESS OR IMPLIED WARRANTY OR CONDITION, OR THAT IN ANY WAY ARISE IN RELATION TO THE PRODUCT. 600FTS-PDS sas 10312023.docx

Neogard®, a part of Hempel  
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - [www.neogard.com](http://www.neogard.com)