

# Product Data Sheet

70420-CA (47JJB)

Integrally Textured Aromatic Urethane, SCAQMD-Compliant



**Description:** 70420-CA (Hempel 47JJB) is a single-component, moisture-cured, integrally textured aromatic urethane.

**Recommended use:** As a waterproofing membrane wear coat and topcoat for the Auto-Gard T vehicular traffic bearing deck coating system.

**Certificates/approvals:** LEED: MRc5, IEQc4.2

**Features:** Meets South Coast Air Quality Management District (SCAQMD) VOC requirements.

**Availability:** Available in North America. Not included in Group Assortment; other regions must confirm.

## Colors and packaging:

70420-CA (47JJB16650)      Gray      5-gallon

## Physical constants:

Tensile strength*	2,500 psi	ASTM D412
Elongation*	350%	ASTM D412
Permanent set	<30%	ASTM D412
Tear resistance	253.3 pli	ASTM D1004
Taber abrasion	39.6 mg/1,000 CS-17	ASTM D4060
Shore A	78	ASTM D2240
Peel adhesion	19.31 pli	ASTM D903
Weight/gallon	10.78 lbs/gal ± 0.25	ASTM D5201
Weight solids	80% ± 3.0%	ASTM D5201
Volume solids	77% ± 2.0%	ASTM D5201
VOC	<100 g/L	ASTM D5201
Viscosity	117 KU	ASTM D562
Flash point		Refer to SDS
Shelf life	1 year	
Cure to recoat at 75°F/23°C, 50% RH	8–12 hours	

*\*Cured properties are exclusive of aggregate. The above tested results are typical values. Individual lots may vary. Further technical information can be found at [www.neogard.com](http://www.neogard.com).*

## Application details:

**Application method:** Squeegee or roller (do not dip and roll from container)

**Thinner (max.vol.):** Hempel 08710 or Acetone may be added not to exceed 10 % by vol. or 12 oz/gal

**Accelerator:** Not recommended

**Mixing:** Mix for 3–5 minutes before applying; Jiffy Mixer paddle recommended

**Cleaning of tools:** Acetone or other VOC compliant multi-purpose solvents. Confirm compliance with Local, State and Federal air quality rules before use.

**Safety:** Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations.

**Application conditions:** Substrate temperature must be between 40°F/4°C and 110°F/32°C.

**Preceding coat:** According to Neogard Guide Specifications.

**Subsequent coat:** According to Neogard Guide Specifications.

**Accelerators and additives:** 7922 (990JB00000): Enhances sag resistance.  
994JB00000 Vanilla Odor mask

# Product Data Sheet

70420-CA (47JJB)

Integrally Textured Aromatic Urethane, SCAQMD-Compliant



**Storage temperature:** Store in a cool area to ensure full shelf life. Recommended temperature: 75°F/23°C.

**Remarks:** Not recommended for constant immersion. Do not apply over asphaltic compounds. For on-grade applications, substrates constructed over unvented metal decks or between-slab applications, contact Neogard Technical Service.

**Note:** 70420-CA is for professional use only.

**Issued by:** Hempel (USA) – 47JJB

This Product Data Sheet (“PDS”) relates to the supplied product (“Product”) and is subject to update from time-to-time. Accordingly, the buyer/applicator should refer to the PDS current as of the time of delivery. In addition to the PDS, the buyer/applicator may receive some or all of the specifications, statements and/or guidelines listed below or available at [www.neogard.com](http://www.neogard.com) (the “Additional Documents”):

No.	Document Description
1	PDS
2	Guide Specification
3	Application Manual
4	Other Technical Support Information (i.e. summary application tables, troubleshooting guides, maintenance manuals, chemical resistance charts and other technical information )

In the event of a conflict between this PDS and the Additional Documents, the conflict shall be resolved in accordance with the order of priority set forth above. In addition, the buyer/applicator should refer to the relevant Safety Data Sheet current as of the time of delivery and available at [www.neogard.com](http://www.neogard.com). Buyer/applicator is responsible for determining the suitability of the intended use of the Product, and Neogard disclaims all responsibility for any use, handling and storage of the Product that is not in accordance with the requirements set forth in the relevant PDS and the Additional Documents. The terms and provisions hereof apply to this PDS, the Additional Documents and any other documents supplied by Neogard in respect of the Product. The Product is supplied and all technical assistance is given subject to the General Conditions of Sale of Hempel Products and/or Services available at [www.hempel.com](http://www.hempel.com). NEOGARD MAKES NO OTHER WARRANTY THAT EXTENDS BEYOND THE WARRANTY REFERENCED THEREIN INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTIES OR CONDITIONS OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. NEOGARD WILL NOT BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR BREACH OF ANY EXPRESS OR IMPLIED WARRANTY OR CONDITION, OR THAT IN ANY WAY ARISE IN RELATION TO THE PRODUCT.

70420-CA-PDS sas 01302023.docx

Neogard®, a part of Hempel  
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - [www.neogard.com](http://www.neogard.com)