

# Chemical Resistance Chart

70714/70715-09 (45062)

General Purpose Epoxy

**Rating Key: 0 = No Effect; 1 = Stains/Dulls Film; 2 = Blisters Film; 3 = Lifts Film**

**Ratings are based on 7-day spot test. Water staining may occur after 7 days of full curing.**

Chemical	Rating	Chemical	Rating
Acetic Acid (10%)	0	Isopropyl Alcohol	0
Acetic Acid (20%)	0	Ketchup	0
Acetic Acid (33%)	0	Lactic Acid (20%)	1
Ammonia (28%)	0	Lactic Acid (50%)	1
Blood	0	Methylisobutyl Ketone	1
Brake Fluid	2	Mineral Spirits	0
Butoxyethanol	2	Motor Oil	0
Butoxyethylacetate	2	Mustard	1
Butyl Alcohol	0	Nitric Acid (30%)	1
Butylacrylate	0	Oleic Acid	1
Calcium Chloride	1	Phenol	2
Chromic Acid (2%)	1	Phosphoric Acid (25%)	1
Diacetone Alcohol	2	Propylene Glycol	1
Diesel Fuel	0	Skydrol	1
Ethyl Acetate	1	Sodium Hypochlorite	1
Ethyl Alcohol	0	Solvent 100	0
Ethylene Glycol	0	Sulphuric Acid (10%)	1
Formic Acid	1	Sulphuric Acid (50%)	1
Gasoline	0	Tall Oil Fatty Acid	1
Hydrobromic (48%)	1	Urine	0
Hydrochloric Acid (37%)	1	Vegetable Oil	0
Hydrofluoric Acid (48%)	2	Vinegar	1

Issued by: Hempel (USA) – 70714/70715-09 CRC

This document is intended for professional use and provides generic advice in respect of the subject matter hereof only. It is not intended to be used as a comprehensive guide. The buyer/applicator should always read the relevant Product Data Sheets ("PDS"), Safety Data Sheets and Guide Specification relating to the applicable products/system. If in doubt, please contact your local Neogard representative for further advice. To the extent relevant, the disclaimer set forth in the relevant PDS or Guide Specification applies to this document. 70714-70715-09-CRC ksk 09022021.docx