

Product Data Sheet

70714/70715-09 — 2K General Purpose Epoxy
45062: Base 45069 : Curing Agent 95075



Description:	70714/70715-09 (Hempel 45062) is a two-component, general purpose, 100% solids epoxy resin.
Recommended use:	Applications over concrete include: High strength overlayment; high-strength dustproofers; high-gloss, high-build protective coating; binder for self-smoothing pigmented and color quartz flooring; low-viscosity binder for trowel-applied mortar flooring systems; high-quality primer for chemical resistant urethane top coats, and/or Neogard waterproofing and flooring systems; low-viscosity binder for trowel-applied mortar and/or patching material; low viscosity binder for crack injection.
Features:	Meets South Coast Air Quality Management District (SCAQMD) VOC requirements.
Certificates/approvals:	LEED: MRc5, IEQc4.2
Availability:	Available in North America. Not included in Group Assortment; other regions must confirm.

Colors and packaging:

70714 (4506900000)	Clear	15- and 3-gallon kits
70714-01 (4506916640)	White	15- and 3-gallon kits
70714-02 (4506916650)	Gray	15- and 3-gallon kits
70714-03 (4506923820)	Tan	15- and 3-gallon kits
70714-04 (4506916670)	Dark Gray	15- and 3-gallon kits
70714-05 (4506957930)	Tile Red	15- and 3-gallon kits
70714-11 (4506916660)	Light Gray	15- and 3-gallon kits
70714-16 (4506919990)	Black	15- and 3-gallon kits
70714-06 (4506949890)	Green	3-gallon kits
70715-09 (9507500000)	NA	Curing agent, included in kits

Some standard colors and/or packaging may have extended lead times and/or minimum quantities. Contact Neogard for additional colors.

Physical constants:

Tensile strength	2,000 psi	ASTM D638
Elongation	40%	ASTM D638
Compressive strength	15,000 psi	ASTM D695
Flexural strength	1,900 psi	ASTM D790
Flexural modulus	62,000 psi	ASTM D790
Water resistance	0.17%	ASTM D570
MVT at 10 mils	0.18 Perm	ASTM E96
Shore D	77	ASTM D2240
Adhesion	400 psi	ASTM D4541
Impact flexibility	Pass at 120 in/lb	ASTM D6905-03
Flammability	Pass	ASTM D635
Taber abrasion	61 mg/1,000 CS-17	ASTM D4060
Weight/gal (mixed)	8.81 lbs/gal	ASTM D1475
Weight solids (mixed)	100%	ASTM D4209
Volume solids (mixed)	100%	Calculated
Viscosity (mixed)	1,250 cps	ASTM D2196
VOC (mixed)	<100 g/L	ASTM 5201
Flash point		Refer to SDS
Shelf life	1 year	
Thin film cure at 75°F/23°C	8–9 hours	
Full cure at 75°F/23°C	7 days	
Full chemical resistance	7 days	

The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at www.neogard.com.

Product Data Sheet

70714/70715-09 — 2K General Purpose Epoxy
45062: Base 45069 : Curing Agent 95075



Application details:

Version, mixed product	45062
Mixing ratio:	Base 45069 : Curing Agent 95079 2 : 1 by volume
Mixing instructions:	Pre-mix base for 3–5 minutes before adding curing agent. Mix for a minimum of 5 minutes before applying. Jiffy Mixer paddle recommended.
Application method:	Roller or squeegee
Thinner:	Coating is to be applied without thinning
Pot life:	25 minutes at 70°F/21°C
Cleaning of tools:	Acetone or other VOC compliant multi-purpose solvents. Confirm compliance with Local, State and Federal air quality rules before use.
Safety:	Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations.
Surface preparation:	According to Neogard Guide Specifications.
Application conditions:	Ambient and surface temperatures must be between 50°F/10°C and 85°F/29°C, and a minimum of 5°F/3°C above dew point.
Preceding coat:	According to Neogard Guide Specifications.
Subsequent coat:	Must be recoated within 24 hours at 70°F/21°C for subsequent coat to properly bond. If the 24-hour recoat window is missed, sand to dull finish before applying subsequent coat(s).
Storage temperature:	Store in a cool area to ensure full shelf life. Recommended temperature: 70°F/21°C.

Note: 70714/70715-09 is for professional use only.

Issued by: Hempel (USA) – 45062

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to update from time-to-time. Accordingly, the buyer/applicator should refer to the PDS current as of the time of delivery. In addition to the PDS, the buyer/applicator may receive some or all of the specifications, statements and/or guidelines listed below or available at www.neogard.com (the "Additional Documents"):

No.	Document Description
1	PDS
2	Guide Specification
3	Application Manual
4	Other Technical Support Information (i.e. summary application tables, troubleshooting guides, maintenance manuals, chemical resistance charts and other technical information)

In the event of a conflict between this PDS and the Additional Documents, the conflict shall be resolved in accordance with the order of priority set forth above. In addition, the buyer/applicator should refer to the relevant Safety Data Sheet current as of the time of delivery and available at www.neogard.com. Buyer/applicator is responsible for determining the suitability of the intended use of the Product, and Neogard disclaims all responsibility for any use, handling and storage of the Product that is not in accordance with the requirements set forth in the relevant PDS and the Additional Documents. The terms and provisions hereof apply to this PDS, the Additional Documents and any other documents supplied by Neogard in respect of the Product. The Product is supplied and all technical assistance is given subject to the General Conditions of Sale of Hempel Products and/or Services available at www.hempel.com. NEOGARD MAKES NO OTHER WARRANTY THAT EXTENDS BEYOND THE WARRANTY REFERENCED THEREIN INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTIES OR CONDITIONS OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. NEOGARD WILL NOT BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR BREACH OF ANY EXPRESS OR IMPLIED WARRANTY OR CONDITION, OR THAT IN ANY WAY ARISE IN RELATION TO THE PRODUCT. 70714-70715-09-PDS ksk 10272021.docx

Neogard®, a part of Hempel
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com