

Description:	FTS 301 (Hempel 888J9) Membrane is a 100% solids, elasticized methacrylate (MMA) resin.
Recommended use:	FTS 301 is used as the base resin to create cove/wall base coats in Neogard FTS acrylic flooring systems. System thickness typically ranges from 1/16" to 1/4" depending on the application technique and performance requirements of the system.
Features:	Cures in 60 minutes. Cures at temperatures ranging from -15°F - 100°F. Creates monolithic cove/wall base to match floor coating. Applied over Neogard FTS 100. Meets South Coast Air Quality Management District (SCAQMD) VOC requirements
Availability:	Available in North America. Not included in Group Assortment; other regions must confirm.

Colors and packaging:

FTS 301 (888J900000G4,4)	Clear	5-gallon pails
--------------------------	-------	----------------

Physical constants:

Tensile Strength	1950 psi	ASTM D638
Tensile Modulus	230,000	ASTM D638
Compressive Strength	8,000 (filled)	ASTM C109
Flexural Strength	3,500	ASTM D790
Water Absorption	.04	ASTM D570
Electrical Resistivity	Volume Resistance (ohm-cm): 10 ¹⁴	ASTM D257
Weight/Gallon (mixed)	8.3 lbs/gal	
Weight Solids (mixed)	100%	ASTM D1475
Volume Solids (mixed)	100%	ASTM D4209
VOC (mixed)	<100 g/L	ASTM D5201
Viscosity (mixed)	12-15 KU	ASTM D562
Flash Point		Refer to SDS
Shelf Life	1 year	
Cure to Recoat at 75°F/23°C, 50% relative humidity	1 hour	

The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at www.neogard.com.

Application details:

Mixing ratio:	Refer to FTS BPO Dosing Chart
Mixing instructions:	Pre-mix base for 3–5 minutes before adding curing agent and fillers (sand or color quartz). Mix for a minimum of 5 minutes before applying. Jiffy Mixer paddle recommended.
Application method:	Roller or notched squeegee
Thinner (max.vol.):	Coating is to be applied without Thinning.
Pot life:	15-20 minutes at 75°F/23°C
Cleaning of tools:	Clean tools with Neogard 800 FTS Cleaning Agent only. Other solvents may contaminate MMA coatings, and cause the coating to cure improperly.

Safety:	Handle with care. Use with adequate ventilation. No smoking, open flames, or sparks should be permitted in and around the working area. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations.
Surface preparation:	According to Neogard Guide Specifications.
Application conditions:	Substrate temperature must be between 40°F/4°C and 110°F/32°C.
Preceding coat:	According to Neogard Guide Specifications.
Subsequent coat:	According to Neogard Guide Specifications.
Storage temperature:	Store material in a cool and dry place out of direct sunlight. Do not store near open flame or ignition source.. Recommended temperature: 75°F/23°C.
Remarks:	<p>Must be protected from UV exposure. Should be applied over a mechanically prepared concrete substrate at a rate allowing for penetration of the concrete. The rate of application will depend on the substrate surface profile and porosity.</p> <p>A second coat of primer mixture may be required on a porous substrate or if the coating appears to be inconsistent.</p>

Note: **FTS 300 is for professional use only.**

Issued by: Hempel (USA) –XXXX

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to update from time-to-time. Accordingly, the buyer/applicator should refer to the PDS current as of the time of delivery. In addition to the PDS, the buyer/applicator may receive some or all of the specifications, statements and/or guidelines listed below or available at www.neogard.com (the "Additional Documents"):

No.	Document Description
1	PDS
2	Guide Specification
3	Application Manual
4	Other Technical Support Information (i.e. summary application tables, troubleshooting guides, maintenance manuals, chemical resistance charts and other technical information)

In the event of a conflict between this PDS and the Additional Documents, the conflict shall be resolved in accordance with the order of priority set forth above. In addition, the buyer/applicator should refer to the relevant Safety Data Sheet current as of the time of delivery and available at www.neogard.com. Buyer/applicator is responsible for determining the suitability of the intended use of the Product, and Neogard disclaims all responsibility for any use, handling and storage of the Product that is not in accordance with the requirements set forth in the relevant PDS and the Additional Documents. The terms and provisions hereof apply to this PDS, the Additional Documents and any other documents supplied by Neogard in respect of the Product. The Product is supplied and all technical assistance is given subject to the General Conditions of Sale of Hempel Products and/or Services available at www.hempel.com. NEOGARD MAKES NO OTHER WARRANTY THAT EXTENDS BEYOND THE WARRANTY REFERENCED THEREIN INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTIES OR CONDITIONS OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. NEOGARD WILL NOT BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR BREACH OF ANY EXPRESS OR IMPLIED WARRANTY OR CONDITION, OR THAT IN ANY WAY ARISE IN RELATION TO THE PRODUCT.

FTS 301 PDS sas 02282023.docx

Neogard®, a part of Hempel
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com