

Product Data Sheet

67BUS

Aluminum Oxide Aggregates



Description: Neogard 67BUS products are aluminum oxide aggregates.

Recommended use: 67BUS aggregates are added to Neogard Floor-Gard HD, Floor-Gard HD Grind & Seal, or other Neogard flooring and waterproofing systems to create a non-skid texture and improve abrasion resistance.

Availability: Available in North America. Not included in Group Assortment; other regions must confirm.

Colors, grits, and packaging:

67BUS99981	White	220 grit	
67BUS99982	White	30 grit	50-lb bags
67BUS99984	White	60 grit	
67BUS99980	Brown	16 grit	

Physical constants:

Grain shape	Angular
Hardness	9.0 Mohs/2,000 Knoop
Specific gravity	3.95 g/cm ³
Oxidation-reduction effects	None
Melting point	3,632°F/2,000°C

These figures apply to all 67BUS products. Other physical constants may differ among 67BUS products. The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at www.neogard.com.

Application details:

Application and mixing: See Neogard Guide Specifications for application instructions and mix ratios.

Safety: Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations.

Storage: Store in a dry area.

Note: **67BUS is for professional use only.**

Issued by: Hempel (USA) – 67BUS

This Product Data Sheet (“PDS”) relates to the supplied product (“Product”) and is subject to update from time-to-time. Accordingly, the buyer/applicator should refer to the PDS current as of the time of delivery. In addition to the PDS, the buyer/applicator may receive some or all of the specifications, statements and/or guidelines listed below or available at www.neogard.com (the “Additional Documents”):

No.	Document Description
1	PDS
2	Guide Specification
3	Application Manual
4	Other Technical Support Information (i.e. summary application tables, troubleshooting guides, maintenance manuals, chemical resistance charts and other technical information)

In the event of a conflict between this PDS and the Additional Documents, the conflict shall be resolved in accordance with the order of priority set forth above. In addition, the buyer/applicator should refer to the relevant Safety Data Sheet current as of the time of delivery and available at www.neogard.com. Buyer/applicator is responsible for determining the suitability of the intended use of the Product, and Neogard disclaims all responsibility for any use, handling and storage of the Product that is not in accordance with the requirements set forth in the relevant PDS and the Additional Documents. The terms and provisions hereof apply to this PDS, the Additional Documents and any other documents supplied by Neogard in respect of the Product. The Product is supplied and all technical assistance is given subject to the General Conditions of Sale of Hempel Products and/or Services available at www.hempel.com. NEOGARD MAKES NO OTHER WARRANTY THAT EXTENDS BEYOND THE WARRANTY REFERENCED THEREIN INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTIES OR CONDITIONS OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. NEOGARD WILL NOT BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR BREACH OF ANY EXPRESS OR IMPLIED WARRANTY OR CONDITION, OR THAT IN ANY WAY ARISE IN RELATION TO THE PRODUCT. 67BUS-PDS ksk 06222021.docx

Neogard®, a part of Hempel
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com