

# Chemical Resistance Chart

70869/70819 Polyaspartic, Clear (5703100050)

70869-01/70819 Polyaspartic, White (5703200010)



Rating Key: 0 = No Effect; 1 = Stains/Dulls Film; 2 = Blisters Film; 3 = Lifts Film  
Ratings are based on 7-day spot test.

70869/70819 Polyaspartic, Clear (5703100050)		70869-01/70819 Polyaspartic, White (5703200010)	
Chemical	Rating	Chemical	Rating
Acetic Acid 36%	1	Acetic Acid 36%	1
Auto Transmission Fluid	0	Auto Transmission Fluid	0
Brake Fluid	1	Brake Fluid	2
Butoxy Ethanol	2	Butoxy Ethanol	1
Diesel Fuel	1	Diesel Fuel	1
Hydrochloric Acid 15%	1	Hydrochloric Acid 15%	1
Hydrochloric Acid 37%	1	Hydrochloric Acid 37%	1
Lactic Acid 20%	1	Lactic Acid 20%	2
Lactic Acid 85%	2	Lactic Acid 85%	2
Methyl Isobutyl Ketone (MIBK)	1	Methyl Isobutyl Ketone (MIBK)	1
Nitric Acid	0	Nitric Acid	1
Skydrol	2	Skydrol	2
Sodium Hydroxide 50%	1	Sodium Hydroxide 50%	0
Sulfuric Acid 10%	0	Sulfuric Acid 10%	1

Issued by: Hempel (USA) – 70869/70819 & 70869-01/70819 CRC

This document is intended for professional use and provides generic advice in respect of the subject matter hereof only. It is not intended to be used as a comprehensive guide. The buyer/applicator should always read the relevant Product Data Sheets ("PDS"), Safety Data Sheets and Guide Specification relating to the applicable products/system. If in doubt, please contact your local Neogard representative for further advice. To the extent relevant, the disclaimer set forth in the relevant PDS or Guide Specification applies to this document. 70869-70819-CRC ksk 09022021.docx

Neogard®, A part of Hempel  
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com