

# Product Data Sheet

7922 (990JB)

Vertical Additive



**Description:** 7922 (Hempel 990JB) is an additive for Neogard urethanes to enhance sag resistance of the coating material.

**Recommended use:** 7922 is used when fluid-applied urethanes are applied to sloped or vertical surfaces.

**Availability:** Available in North America. Not included in Group Assortment; other regions must confirm.

## Colors and packaging:

7922 (990JB00000)      NA      1/2 pint cans

## Physical constants:

Weight/gallon	9.1 lbs/gal	ASTM D1475
Weight solids	100%	ASTM D4209
Volume solids	100%	Calculated
VOC	0.0 g/L	EPA Method 24
Viscosity	100 cps	ASTM D2196
Flash point	> 250°F (121°C)	ASTM D3278
Shelf life	1 year	
Cure time, 75°F/23°C, 50% relative humidity	24 hours	TT-S-0023OA
Pot life (mixed with urethane coating, 90–120 minutes 75°F/23°C, 50% relative humidity)		Calculated

*The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at [www.neogard.com](http://www.neogard.com).*

## Application details:

7922 can be used for the following urethane coating products. Induction time: 30 minutes.

Product:	7922 per 5 gallons:	Sag resistance (mils):
7430 (57040)	2 x 1/2 pints	14–16
7435 (57040)	2 x 1/2 pints	14–16
70611 series (475JB)	1/2 pint	>50
70620 (473JB)	1/2 pint	>50
70410 (45010)	1/2 pint	14 -16

**Safety:** Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations.

# Product Data Sheet

7922 (990JB)

Vertical Additive



Note: **7922 (990JB) is for professional use only.**

Issued by: Hempel (USA) – 990JB

This Product Data Sheet (“PDS”) relates to the supplied product (“Product”) and is subject to update from time-to-time. Accordingly, the buyer/applicator should refer to the PDS current as of the time of delivery. In addition to the PDS, the buyer/applicator may receive some or all of the specifications, statements and/or guidelines listed below or available at [www.neogard.com](http://www.neogard.com) (the “Additional Documents”):

No.	Document Description
1	PDS
2	Guide Specification
3	Application Manual
4	Other Technical Support Information (i.e. summary application tables, troubleshooting guides, maintenance manuals, chemical resistance charts and other technical information )

In the event of a conflict between this PDS and the Additional Documents, the conflict shall be resolved in accordance with the order of priority set forth above. In addition, the buyer/applicator should refer to the relevant Safety Data Sheet current as of the time of delivery and available at [www.neogard.com](http://www.neogard.com). Buyer/applicator is responsible for determining the suitability of the intended use of the Product, and Neogard disclaims all responsibility for any use, handling and storage of the Product that is not in accordance with the requirements set forth in the relevant PDS and the Additional Documents. The terms and provisions hereof apply to this PDS, the Additional Documents and any other documents supplied by Neogard in respect of the Product. The Product is supplied and all technical assistance is given subject to the General Conditions of Sale of Hempel Products and/or Services available at [www.hempel.com](http://www.hempel.com). NEOGARD MAKES NO OTHER WARRANTY THAT EXTENDS BEYOND THE WARRANTY REFERENCED THEREIN INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTIES OR CONDITIONS OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. NEOGARD WILL NOT BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR BREACH OF ANY EXPRESS OR IMPLIED WARRANTY OR CONDITION, OR THAT IN ANY WAY ARISE IN RELATION TO THE PRODUCT. 7922-PDS ksk 04122021.docx

Neogard®, a part of Hempel  
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - [www.neogard.com](http://www.neogard.com)