

PART 1 GENERAL

1.1 SUMMARY

- A. Provide labor, materials, equipment and supervision necessary to install a highly durable floor coating system as outlined in this specification.
- B. The manufacturer's application instructions for each product used are considered part of this specification and should be followed at all times.
- C. Related Sections:
 - 1. Section 03 30 00: Cast-in-Place Concrete
 - 2. Section 07 90 00: Joint Protection
 - 3. Section 07 95 00: Expansion Control

1.2 SYSTEM DESCRIPTION

- A. Floor-Gard HD Grind & Seal System shall be a complete system of compatible materials supplied by Neogard to create a high performance, seamless, durable, floor coating system.
- B. Floor-Gard HD Grind & Seal System shall be designated for application on the specific type of substrate indicated on the drawings.

1.3 SUBMITTALS

- A. Technical Data: Submit manufacturer's product data, Safety Data Sheets (SDS) and installation instructions.
- B. Samples: Submit samples of the Floor-Gard HD Grind & Seal System floor coating system. Samples shall be construed as examples of finished color and texture of the system only.
- C. Applicator Approval: Submit letter from manufacturer stating applicator is approved to install the Floor-Gard HD floor coating system.
- D. Warranty: Submit copy of manufacturer's standard sample warranty, identifying the terms and conditions stated in section 1.7 Warranty.

1.4 QUALITY ASSURANCE

- A. Supplier Qualifications: Floor-Gard HD Grind & Seal System, as supplied by Neogard, is approved for use on this project.
- B. Applicator Qualifications: Applicators shall be approved to install specified system.
- C. Requirement of Regulatory Agencies: Specified materials shall meet existing Federal, State and local VOC regulations.
- D. Field Sample:
 - 1. Install a field sample of at least 100 square feet at the project site or pre-selected area as agreed to by owner's representative, applicator and manufacturer.
 - 2. Apply material in accordance with manufacturer's written application instructions.
 - 3. Field sample will be standard for judging color and texture on remainder of project.
 - 4. Maintain field sample during construction for workmanship comparison.
 - 5. Do not alter, move, or destroy field sample until work is completed and approved by Owner's representative.

1.5 DELIVERY, STORAGE AND HANDLING

- A. Delivery: Materials shall be delivered in original sealed containers, clearly marked with supplier's name, brand name and type of material.

- B. Storage and Handling: Recommended material storage temperature is 75°F/23°C. Water based products must be protected from freezing. Handle products to prevent damage to container. All materials shall be stored in compliance with local fire and safety requirements. Do not store at high temperatures or in direct sunlight.
- C. Read and follow the SDS and container labels for detailed health and safety information.

1.6 PROJECT CONDITIONS

- A. Proceed with application of materials only when substrate temperature is above 50°F/10°C. Attempt to maintain a minimum substrate temperature of 50°F/10°C for a minimum of 48 hours before, during, and after installation, or until cured.
- B. Substrates must have a properly installed, effective vapor barrier.
- C. Only install materials if surface to receive coating is clean and dry.
- D. Coordinate work with other trades. Applicator shall have sole right of access to specified area for time needed to complete the application and allow system to cure adequately.
- E. Protect adjacent surfaces from damage resulting from installation of the system. If necessary, mask and/or cover adjacent surfaces, fixtures, equipment, etc. by suitable means.
- F. Provide adequate ventilation.
- G. Provide a suitable work station to mix coating materials.
- H. Maintain work area in a neat and orderly condition, removing empty containers, rags and trash daily from the site.

1.7 WARRANTY

- A. Upon request, Neogard shall offer a manufacturer's 5 year material warranty for institutional, commercial, industrial, and high-rise/multi-family residential projects only, upon substantial completion of the application and receipt of a properly executed warranty request form.

PART 2 MATERIALS

2.1 MANUFACTURER

- A. Neogard, a part of Hempel, 2728 Empire Central, Dallas, TX 75235, (800) 321-6588, www.neogard.com.

2.2 MATERIALS

- A. First and Second Coats:
 - 1. 70900/70910 (47DJB) series water-based urethane, gloss finish.
 - 2. 70901/70910 (47VJB) series water-based urethane, semi-gloss finish.
- B. Aggregate: #220 grit aluminum oxide.

2.3 MATERIAL PERFORMANCE CRITERIA

- A. Typical physical properties of cured 70900/70910 series urethane used on this project are:
 - 1. Impact Resistance, ASTM D2794, 120 lbs/in
 - 2. Taber Abrasion, ASTM D4060, 15 mg (1,000 CS-17)
 - 3. Pencil Hardness, ASTM D3363, 4H Gouge
- B. Typical physical properties of cured 70902/70910 urethane used on this project are:
 - 1. Taber Abrasion, ASTM D4060, 20 mg (1,000 CS-17)
 - 2. Pencil Hardness, ASTM D3363, 4H Gouge

- C. Typical physical properties of cured 70901/70910 urethane used on this project are:
 - 1. Impact Resistance, ASTM D2794, 160 lbs/in
 - 2. Taber Abrasion, ASTM D4060, 67 mg (1,000 CS-17)
 - 3. Pencil Hardness, ASTM D3363, 4H Gouge
- D. The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at www.neogard.com.

2.4 ACCESSORIES

- A. Miscellaneous materials such as cleaning agents, adhesives, sealants, backer rods, and others shall be compatible with the specified interior wall and ceiling coating system.

2.5 MIXING

- A. Comply with manufacturer's instructions for mixing procedures.

PART 3 EXECUTION

3.1 EXAMINATION

- A. Verify that the work done under other sections meets the following requirements:
 - 1. That the concrete deck surface is free of ridges and sharp projections, sound and dry.
 - 2. That the concrete was cured for a minimum of 28 days. (Minimum of 3,500 psi compressive strength). The use of concrete curing agents, if any, shall be of the sodium silicate base only; others require written approval by Neogard.
 - 3. That damaged areas of the concrete substrate be restored to match adjacent areas. Use 70714/70715 epoxy and oven-dry silica aggregate approved by Neogard for filling and leveling at a ratio of one part epoxy mixed with four parts aggregate by volume.
 - 4. That due to hydrostatic, capillary and moisture vapor pressure, substrates in contact with ground must have a properly installed, effective vapor barrier. Moisture vapor emission of concrete not to exceed 15 lbs/1,000 sq. ft./24 hrs, when tested by the quantitative calcium chloride test method (ASTM F1869).

3.2 PREPARATION

- A. Cleaning: Surfaces contaminated with oil or grease shall be vigorously scrubbed with a power broom and a strong non-sudsing detergent. Thoroughly wash, clean, and dry. Areas where oil or other contaminants penetrate deep into the concrete may require removal by mechanical methods. Do not apply materials unless surface is clean and dry.
- B. Shot-Blasting: Required surface preparation method for remedial construction is also the preferred method for new construction. Mechanically prepare surface by shot-blasting to industry standard surface texture (ICRI's CSP 3-4) without causing additional surface defects in substrate. Shot-blasting does not remove deep penetrating oils, grease, tar or asphalt stains. Proper cleaning procedures should be followed to ensure proper bonding of the deck coating. Note: If shot-blasting is not practical, contact Neogard Technical Service.
- C. Mechanical Abrading: If surface preparation is done by diamond grinding, surface texture should have the finish appearance of 180 or 220 grit sand paper.
- D. Cracks: After shotblasting, fill all non-moving cracks with 70714/70715 epoxy, mixed with P1934 fumed silica to form a paste. The mix ratio is one part 70714/70715 epoxy to 3 parts P1934 fumed silica by volume.
- E. Control and Cold Joints: Fill control and cold joints flush with 70718/70719 flexible epoxy at 3/4" depth. Install backer rod if necessary to limit depth to 3/4".
- F. Expansion and Isolation Joints: Expansion and isolation joints \leq 1" in width, shall be sealed with 70991 sealant. Sealant shall be applied to inside of joint only, not applied to floor surface.

3.3 APPLICATION

- A. Factors That Affect Dry Film Thickness: Volume solids, thinning, surface profile, application technique and equipment, overspray, squeegee, brush and roller wet out, container residue, spills and other waste are among the many factors that affect the amount of wet coating required to yield proper dry film thickness. To ensure that specified dry film thickness is achieved, use a wet mil gauge to verify actual thickness of wet coating applied, adjusting as needed for those factors which directly affect the dry film build.
- B. First Coat: Mix 70900/70910 gloss or 70901/70910 semi-gloss at a ratio of 3:1 by volume for three minutes. Reduce the mix 5% with water. Apply at a rate of 200–267 sf/gal. (6–8 mils WFT to yield 3–6 mils DFT). Allow to cure until tack free for 4–6 hours at 75°F/23°C.
 - 1. First Coat must be recoated within 24 hours of application at 70°F/21°C for Second Coat to properly bond. If the 24-hour recoat window is missed, sand First Coat to dull finish before applying Second Coat.
- C. Second Coat: Mix 70900/70910 gloss or 70901/70910 semi-gloss at a ratio of 3:1 by volume for three minutes. Add 24 ounces of #220 grit aluminum oxide by volume per mixed gallon and apply at a rate of 400–450 sf/gal. Allow to cure for 4–6 hours at 75°F/23°C.
- D. Do not exceed 24 hours between topcoat applications. If this recoat window is missed, surface will need to be lightly abraded.
- E. Applicator is responsible for applying sufficient coating to the substrate.

3.4 CLEANING

- A. Remove debris resulting from completion of coating operation from the project site.

3.5 PROTECTION

- A. After completion of application, do not allow contact with coated surfaces for a period of at least 48 hours at 75°F/23°C and 50% relative humidity, or until completely cured.

END OF SECTION

Issued by: Hempel (USA) – Neogard Floor-Gard Grind & Seal System

This Guide Specification (“**Guide Spec**”) relates to the supplied products/system (“**System**”) and is subject to update from time-to-time. Accordingly, the buyer/applicator should refer to the Guide Spec current as of the time of delivery. In addition to the Guide Spec, the buyer/applicator may receive some or all of the specifications, statements and/or guidelines listed below or available at www.neogard.com (the “**Additional Documents**”):

No.	Document Description
1	PDS
2	Guide Specification
3	Application Manual
4	Other Technical Support Information (i.e. summary application tables, troubleshooting guides, maintenance manuals, chemical resistance charts and other technical information)

In the event of a conflict between this Guide Spec and the Additional Documents, the conflict shall be resolved in accordance with the order of priority set forth above. In addition, the buyer/applicator should refer to the relevant Safety Data Sheets current as of the time of delivery of the System and available at www.neogard.com. Buyer/applicator is responsible for determining the suitability of the intended use of the System, and Neogard disclaims all responsibility for any use, handling and storage of any components of the System that are not in accordance with the requirements set forth in the relevant PDS(s), this Guide Spec and the Additional Documents. The terms and provisions hereof apply to this Guide Spec, the Additional Documents and any other documents supplied by Neogard in respect of the System. The System is supplied and all technical assistance is given subject to the General Conditions of Sale of Hempel Products and/or Services available at www.hempel.com. **NEOGARD MAKES NO OTHER WARRANTY THAT EXTENDS BEYOND THE WARRANTY REFERENCED THEREIN INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTIES OR CONDITIONS OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. NEOGARD WILL NOT BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR BREACH OF ANY EXPRESS OR IMPLIED WARRANTY OR CONDITION, OR THAT IN ANY WAY ARISE IN RELATION TO THE SYSTEM.**
FloorGardHDGSS-GSCSI ksk 11012021.docx