

Product Data Sheet

600 RTS (95UJB) PMMA/PUMA BPO Initiator



- Description:** 600 RTS (Hempel 95UJB) is a fine, granular powder.
- Recommended use:** 600 RTS is used as an initiator/curing agent for Neogard PMMA/PUMA coating products.
- Features:** Easy to handle
Easy dispersion in PMMA/PUMA liquids
Dissolves quickly
- Availability:** Available in North America. Not included in Group Assortment. Availability subject to confirmation.

Colors and packaging:

600 RTS (95UJB00000) White 10-lb pail

Physical constants:

Assay 49.0%–51.0%
Water 2.5% maximum

The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at www.neogard.com.

Application details:

- Mixing:** Jiffy Mixer preferred. Mix with 100 RTS, 200 RTS, 300 RTS, or 400 RTS for 30–45 seconds or until completely mixed. Note: Extended mixing time will shorten working time of the material.
- Dosage rate:** Refer to the dosage chart below, or on 100 RTS, 200 RTS, 300 RTS, and 400 RTS Product Data Sheets for correct dosage. Dosage rates change based upon ambient air temperature.
- Safety:** Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations.
- Storage temperature:** Store at or below 77°F (25°C). Protect against direct sunlight.

BPO Initiator Dosage by Ambient Air Temperature (fluid ounces per gallon)													
Product	30°F (-1°C)	35°F (2°C)	40°F (4°C)	45°F (7°C)	50°F (10°C)	55°F (13°C)	60°F (16°C)	65°F (18°C)	70°F (21°C)	75°F (24°C)	80°F (27°C)	85°F (29°C)	90°F (32°C)
100 RTS	12	11	10	9	8	7	6	5	4	3.5	3	2.5	2
200 RTS	12	11	10	9	8	7	6	5	4	3.5	3	2.5	2
300 RTS	12	11	10	9	8	7	6	5	4	3.5	3	2.5	2
400 RTS	6	6	5	5	5	4	4	4	3	3	3	2.5	2

Product Data Sheet

600 RTS (95UJB)

PMMA/PUMA BPO Initiator



Note: **600 RTS is for professional use only.**

Issued by: Hempel (USA) – 95UJB

This Product Data Sheet supersedes those previously issued.

Manufacturer warrants that the physical properties of the product reported above will meet the standards and deviations of the associated ASTM test method. MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. 600RTS-PDS ksk 07302020.docx

Neogard®, a part of Hempel
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com