## Product Data Sheet 67BUS99984

**CG Grout** 



Description:	CG Grout (67BUS99984) is a silica quartz sand aggregate.
Recommended use:	CG Grout is used as a high-build underlayment for leveling or sloping in conjunction with Neogard fluid-applied flooring or waterproofing systems.
Features:	Consistent, uniform grain shapes and particle size distribution. Excellent placement and compaction, which lead to excellent mechanical properties. Resists abrasion in high traffic and wear areas. Provides stability for the flooring system.
Availability:	Available in North America. Not included in Group Assortment; other regions must confirm.

## Colors and packaging:

67BUS99984	Neutral	40-lb bag
------------	---------	-----------

## **Physical constants:**

Grain shape	Sub Round/ Sub Angular
Grain size	12-200 mesh
Hardness	≥7.0 Mohs
Moisture content	<0.1%
Specific gravity	2.65 g/cm <sup>3</sup>
Bulk density, loose	92 - 95 lbs/ft <sup>3</sup>
Bulk density, compacted	98 - 100 lb/ft <sup>3</sup>
<b>Sieve Analysis</b> 16 20 30 40 50 70 100 140	Percent Retained 11.5 9.4 3.3 6.0 9.5 9.7 3.8 2.4 The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at www.neogard.com.

## Application details:

Application and mixing:	Primer: Apply 70714/70715 clear epoxy at a rate of 250–300 square feet per gallon. CG Grout can be applied directly over wet or cured primer.
	Mix 4 parts of CG Grout with 1 part of 70714/70715 clear or pigmented epoxy by volume.
	Apply by trowel or screed to desired thickness.
	One 3 gallon kit of mixed 70714/70715 epoxy with 5 bags of CG Grout will cover 25 square feet at 1 inch thick, or 8.3 square feet at 3 inches thick.
	Note: Maximum depth in one application or lift is 3 inches. Applications or lifts greater than 3 inches can cause blistering or delamination.
Safety:	Handle with care. Before and during use, observe all safety labels on packaging and paint containers, Consult Neogard Safety Data Sheets and follow all local or national safety regulations.
Storage:	Store in a dry area.



Note:

CG Grout is for professional use only.

Issued by:

Hempel (USA) - 67BUS99984

This Product Data Sheet supersedes those previously issued.

Manufacturer warrants that the physical properties of the product reported above will meet the standards and deviations of the associated ASTM test method. MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. 67BUS99984-PDS ksk 07082020.docx

Neogard<sup>®</sup>, a part of Hempel 2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com

Issued: July 2020