

# Product Data Sheet

## 7032 series (61AJB, 61BJB)

### Acrylic Elastomeric Patching Compound



**Description:** 7032 series (Hempel 61AJB and 61BJB) is an acrylic, water-borne, elastomeric patching compound. It is available in textured and smooth versions.

**Recommended use:** 7032 series is used to detail cracks and construction joints in masonry walls.

**Availability:** Available in North America. Not included in Group Assortment; other regions must confirm.

#### Colors and packaging:

7032-03 (61AJB99980)	White (textured)	1-gallon
7032-04 (61BJB99980)	White (smooth)	1-gallon

#### Physical constants:

Adhesion	5 lbs/in	ASTM D903
Weight/Gallon	13.5 lbs/gal	ASTM D1475
Weight Solids	81%	ASTM D4209
Volume Solids	69%	Calculated
VOC	75 g/l	EPA Method 24
Viscosity	Paste	ASTM D562
Flash Point	> 212°F (100°C)	ASTM D3278
Dry Time (60 wet mils)	4 hrs @ 75°F (23°C), 50% RH	ASTM D5895

*The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at [www.neogard.com](http://www.neogard.com).*

#### Application details:

Application method: Knife or trowel  
Cleaning of tools: Water

**Safety:** Handle with care. Avoid contact with bare skin. Wear gloves to prevent contact. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations.

**Surface preparation:** According to Neogard system Guide Specifications.

**Subsequent coat:** According to Neogard system Guide Specifications.

**Storage temperature:** Store in a cool area (75°F, 23°C). Must be stored above freezing (32°F, 0°C).

**Note:** 7032 series is for professional use only.

Issued by: Hempel (USA) – 61AJB, 61BJB

This Product Data Sheet supersedes those previously issued.

Manufacturer warrants that the physical properties of the product reported above will meet the standards and deviations of the associated ASTM test method. MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. Document8

Neogard®, a part of Hempel  
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - [www.neogard.com](http://www.neogard.com)