

Product Data Sheet

70420 (47HJB)

Integrally Textured Aromatic Urethane



Description:	70420 (Hempel 47HJB) is an integrally textured, single component moisture-cured, aromatic urethane.
Recommended use:	As a waterproofing membrane wear coat and topcoat for the Auto-Gard T vehicular traffic bearing deck coating system.
Certificates/approvals:	LEED: MRc4, MRc5 Miami-Dade: NOA No.: 15-0421.01
Availability:	Available in North America. Not included in Group Assortment; other regions must confirm.

Colors and packaging:

70420 (47HJB16650)	Gray	5-gallon
70420-041 (47HJB16680)	Charcoal Gray	

Physical constants:

Tensile Strength*	2,500 psi	ASTM D412
Elongation*	350%	ASTM D412
Permanent Set	<30%	ASTM D412
Tear Resistance	253.3 pli	ASTM D1004
Taber Abrasion	39.6 mg	ASTM D4060
Shore A	78	ASTM D2240
Peel Adhesion	19.31 pli	ASTM D903
Weight/Gallon	10.32 lbs/gal	ASTM D5201
Weight Solids	83.7%	ASTM D5201
Volume Solids	77%	ASTM D5201
VOC	201 g/L	ASTM D5201
Viscosity	117 KU	ASTM D562
Flash Point	110°F (32°C)	ASTM D56
Shelf Life	1 year	
Cure to Recoat at 75°F (23°C), 50% RH	8–12 hours	

**Cured properties are exclusive of aggregate. The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at www.neogard.com.*

Application details:

Application method:	Squeegee or roller (do not dip and roll from container)
Thinner (max.vol.):	Hempel's Thinner 08080 (xylene) (10%)
Mixing:	Mix for 3–5 minutes before applying; Jiffy Mixer paddle recommended
Cleaning of tools:	Hempel's Thinner 08080 (xylene)

Safety: Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations.

Application conditions: Substrate temperature must be between 40°F/4°C and 110°F/32°C.

Preceding coat: According to Neogard Guide Specifications.

Subsequent coat: According to Neogard Guide Specifications.

Product Data Sheet

70420 (47HJB)

Integrally Textured Aromatic Urethane



Note: **70420 is for professional use only.**

Issued by: Hempel (USA) – 47HJB

This Product Data Sheet supersedes those previously issued.

Manufacturer warrants that the physical properties of the product reported above will meet the standards and deviations of the associated ASTM test method. MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. 70420-PDS ksk 07102020.docx

Neogard®, a part of Hempel
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com