Product Data Sheet

70690 (47CJB) Aromatic Urethane Roofing Mastic



Description: 70690 (Hempel 47CJB) is a single-component, moisture-cured, aromatic polyurethane mastic.

Recommended use: For repairs and detailing on polyurethane foam, concrete, metal, modified bitumen, and single-ply

roof systems.

Availability: Available in North America. Not included in Group Assortment; other regions must confirm.

Colors and packaging:

70690 (47CJB16640) White 3-gallon pail

Physical constants:

Tensile strength 515 psi ASTM D412 ASTM D412 Elongation 510% Permanent set 6.25% ASTM D412 Tear resistance 0.44 lbs **ASTM D1004** Water resistance 3.7% at 7 days ASTM D471 Shore A **ASTM D2240** 57

 Weight/gallon
 10.77 lb/gal
 ASTM D1475

 Weight solids
 87.09
 ASTM D2369

 Volume solids
 75.3
 Calculated

 VOC
 210g/L
 ASTM D3960

 Flash point
 220°F (104°C)
 ASTM D56

Cure time 24 hours Shelf life at 70–90°F (21–32°C) 6 months

The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further

technical information can be found at www.neogard.com.

Application details:

Application method: Knife, roller, gun, or other appropriate tools/methods

Thinner (max.vol.): 7055 Odorless Reducer (086JB) or Hempel's Thinner 08080 (xylene) (10%) Cleaning of tools: 7055 Odorless Reducer (086JB) or Hempel's Thinner 08080 (xylene)

Safety: Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels

on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or

national safety regulations.

Surface preparation: According to Neogard Guide Specifications.

Application conditions: Substrate temperature must be above 50°F (10°C) and/or below 110°F (43°C), and more than 5°F

(3°C) above the dew point and rising. Maximum relative humidity: 80%.

Preceding coat: According to Neogard Guide Specifications.

Subsequent coat: According to Neogard Guide Specifications.

Accelerators and additives: 7922 (990JB00000): Vertical additive, enhances sag resistance.

7931 (9905500000): Fast accelerator for use in low humidity environments.

7986 (994JB00000): Odor mask, synthetic vanilla scent.

7987 (995JB00000): Odor mask, orange scent.

Storage temperature: Store in a cool area to ensure full shelf life. Recommended temperature: 75°F (23°C).

Issued: March 2020 Page: 1/2

Product Data Sheet

70690 (47CJB) Aromatic Urethane Roofing Mastic



Note: 70690 is for professional use only.

Issued by: Hempel (USA) – 47CJB

This Product Data Sheet supersedes those previously issued.

Manufacturer warrants that the physical properties of the product reported above will meet the standards and deviations of the associated ASTM test method.

MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY
IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Buyer must make its own determination of
the suitability of any product for its use, whether such product is used alone or in combination with other materials. To the extent this or any of Manufacturer's products is
proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE
LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON
OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS. Nothing contained herein shall be construed to
constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed
as an employee or agent of Manufacturer. 70690-PDS ksk 03252020.docx

Neogard®, a part of Hempel 2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com

Issued: March 2020 Page: 2/2