

Product Data Sheet

70724/70715 — Epoxy Mastic

251J1: Base 251J9 : Curing Agent 95073



Description:	70724/70715 (Hempel 251J1) is a two-component, 100% mastic epoxy resin.
Recommended use:	As a base coat in the Neogard Wall-Gard HD system, and as a grout material for 1/4" trowel systems. Also used as a semi-high-gloss, high-build protective coating that can be spray applied onto vertical surfaces at 15 to 30 mils in one pass.
Features:	No amine blush when used in humid environments. Excellent chemical and abrasion resistance. Meets U.S.D.A. requirements for incidental food contact. Meets South Coast Air Quality Management District (SCAQMD) VOC requirements.
Certificates/approvals:	LEED: MRC5, IEQc4.2
Availability:	Available in North America. Not included in Group Assortment; other regions must confirm.

Colors and packaging:

70724-01 (251J910000)	Gray	
70724-11 (251J916660)	Light Gray	4-gallon kit
70715 (9507300000)	NA	

Physical constants:

Tensile Strength	5,000 psi	ASTM D638
Elongation @ Break	10%	ASTM D638
Water Resistance	0.15%	ASTM D570
MVT @ 10 mils	0.15	ASTM E96
Taber Abrasion	50 mg/1,000 CS-17	ASTM D4060
Shore D	80	ASTM 2240
Adhesion	300 psi	ASTM D4541
Flammability	Pass	ASTM D635
Weight/Gallon (mixed)	12.4 lbs/gal	ASTM D1475
Weight Solids (mixed)	99.8%	ASTM D4209
Volume Solids (mixed)	99.6%	Calculated
Viscosity (mixed)	5,000 cps	ASTM D2196
Flash Point	>205°F	ASTM D3278
VOC (mixed)	<5 g/L	EPA Method 24

The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at www.neogard.com.

Application details:

Version, mixed product	251J1
Mixing ratio:	Base 251J9 : Curing Agent 95073 3 : 1 by volume
Mixing instructions:	Pre-mix base for 3–5 minutes before adding curing agent. Mix for a minimum of 5 minutes before applying. Jiffy Mixer paddle recommended.
Application method:	Roller, squeegee, or spray
Thinner (max.vol.):	7055 Odorless Reducer (086JB) or HEMPEL'S THINNER 08080 (xylene) (10%)
Pot life:	90 minutes at 75°F (23°C)
Cleaning of tools:	7055 Odorless Reducer (086JB) or HEMPEL'S THINNER 08080 (xylene)

Safety: Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations.

Surface preparation: According to Neogard Guide Specifications.

Product Data Sheet

70724/70715 — Epoxy Mastic

251J1: Base 251J9 : Curing Agent 95073



Application conditions:	Ambient temperature must be between 50°F (10°C) and 85°F (29°C), and a minimum of 5°F (3°C) above dew point.
Preceding coat:	According to Neogard Guide Specifications.
Subsequent coat:	According to Neogard Guide Specifications.
Storage temperature:	Store in a cool area to ensure full shelf life. Recommended temperature: 70°F (21°C).
Remarks:	Not UV-stable; apply a UV-resistant topcoat if exposed.

Note: **70724/70715 is for professional use only.**

Issued by: Hempel (USA) – 251J1

This Product Data Sheet supersedes those previously issued.

Manufacturer warrants that the physical properties of the product reported above will meet the standards and deviations of the associated ASTM test method. MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. 70724-70715-PDS ksk 03052020.docx

Neogard®, a part of Hempel
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com