

Product Data Sheet

70734/70735 — Low-Yellowing Epoxy
45040: Base 45049 : Curing Agent 95049



Description: 70734/70735 (Hempel 45040) is a two-component, 100% solids hybrid epoxy resin.

Recommended use: Used primarily as a finish coat for NeoQuartz decorative flooring systems or as the primary wearing surface when applied to primed concrete. May also be used on the following prepared substrates: epoxy primed concrete; troweled resinous flooring; decorative floor systems; self-leveling systems.

Features: Minimal yellowing. Reduced UV degradation. Resists impact and abrasion. Very low odor. Can be used as a low-VOC alternative to chemical resistant urethanes.
Meets U.S.D.A. requirements for incidental food contact.
Meets South Coast Air Quality Management District (SCAQMD) VOC requirements.

Certificates/approvals: LEED: MRc5, IEQc4.2

Availability: Available in North America. Not included in Group Assortment; other regions must confirm.

Colors and packaging:

70734 (4504900000)	Clear	15- and 3-gallon kits
70735 (9504900000)	NA	

Physical constants:

Compressive Strength	11,000 psi	ASTM D695
Tensile Strength	8,000 psi	ASTM D638
Elongation @ Break	14%	ASTM D638
Flexural Strength	10,000 psi	ASTM D790
Flexural Modulus	400,000 psi	ASTM D790
Modulus of Elasticity	170,000 psi	ASTM D790
Shore D	82	ASTM D2240
Adhesion	400 psi	ASTM D4541
Water Resistance	<2%	ASTM D570
MVT @ 20 mils	0.10 Perm	ASTM E96
Flammability	Pass	ASTM D635
Taber Abrasion	89 mg/1,000 cycles CS-17	ASTM D4060
Weight/Gallon (mixed)	9.1 lbs/gal	ASTM D1475
Weight Solids (mixed)	100%	ASTM D4209
Volume Solids (mixed)	100%	Calculated
Viscosity (mixed)	500 cps	ASTM D2196
Flash Point	>205oF	ASTM D3278
VOC (mixed)	<10 g/L	EPA Method 24
Shelf Life	1 year	
Thin Film Cure	12–16 hours	
Light Traffic Use	24 hours	
Full Cure @ 75°F (23°C)	7 days	

The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at www.neogard.com.

Application details:

Version, mixed product **45040**

Mixing ratio: Base 45049 : Curing Agent 95049
2 : 1 by volume

Mixing instructions: Pre-mix base for 3–5 minutes before adding curing agent. Mix for a minimum of 5 minutes before applying. Jiffy Mixer paddle recommended.

Application method: Roller/Rake/Squeegee/Notched squeegee

Thinner (max.vol.): 7055 Odorless Reducer (086JB) or HEMPEL'S THINNER 08080 (xylene) (10%)

Pot life: 30 minutes at 75°F (23°C)

Cleaning of tools: 7055 Odorless Reducer (086JB) or HEMPEL'S THINNER 08080 (xylene)

Product Data Sheet

70734/70735 — Low-Yellowing Epoxy
45040: Base 45049 : Curing Agent 95049



Safety:	Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations.
Surface preparation:	According to Neogard Guide Specifications.
Application conditions:	Ambient temperature must be between 50°F (10°C) and 85°F (29°C), and a minimum of 5°F (3°C) above dew point.
Preceding coat:	According to Neogard Guide Specifications.
Subsequent coat:	According to Neogard Guide Specifications.
Storage temperature:	Store in a cool area to ensure full shelf life. Recommended temperature: 70°F (21°C).
Remarks:	For interior use only.

Note: **70734/70735 is for professional use only.**

Issued by: Hempel (USA) – 45040

This Product Data Sheet supersedes those previously issued.

Manufacturer warrants that the physical properties of the product reported above will meet the standards and deviations of the associated ASTM test method. MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. 70734-70735-PDS ksk 03052020.docx

Neogard®, a part of Hempel
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com