

Product Data Sheet

70750/70751 — Low-Modulus Epoxy
472JB: Base 472J9 : Curing Agent 95YJB



Description:	70750/70751 (Hempel 472JB) is a two-component, 100% solids, moisture tolerant, flexible, low-modulus epoxy.
Recommended use:	As a binder for epoxy overlay systems and for use as a wearing course with aggregate for Neogard traffic bearing coating systems
Features:	Moisture tolerant. Excellent viscosity for leveling.
Availability:	Available in North America. Not included in Group Assortment; other regions must confirm.

Colors and packaging:

70750 (472J900000)	Clear	15-gallon kit
70751 (95YJB00000)	Clear	

Physical constants:

Tensile strength	1,362 psi ± 100	ASTM D638
Elongation	81% ± 10	ASTM D638
Flexural strength	1,100 psi	ASTM D790
Taber abrasion	60 mg/1,000 CS-17	ASTM D4060
Shore D	65	ASTM D2240
Modulus of elasticity	42,000 psi	ASTM D790
Adhesion to concrete	960 psi	ASTM D4541
Water resistance	1.3% at 24 hours	ASTM D570
Weight/gallon (mixed)	8.77 lbs/gal	ASTM D1475
Weight solids (mixed)	100%	ASTM D2369
Volume solids (mixed)	100%	ASTM D3960
VOC (mixed)	9.66 g/L (0.08 lbs/gal)	EPA Method 24
Flash point	271°F/133°C	ASTM D3278
Shelf life	6 months	
Tack-free time at 73°F/22°C	4 hours	ASTM D5894

The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at www.neogard.com.

Application details:

Version, mixed product	472JB
Mixing ratio:	Base 472J9 : Curing Agent 95YJB 2 : 1 by volume; mix for 3–5 minutes before applying
Application method:	Roller/Rake/Squeegee/Notched squeegee
Pot life:	30 minutes at 75°F (23°C)
Cleaning of tools:	7055 Odorless Reducer (086JB) or Hempel's Thinner 08080 (xylene)

Safety: Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations.

Surface preparation: According to Neogard Guide Specifications.

Application conditions: Ambient temperature must be between 40°F (4°C) and 100°F (37°C), and a minimum of 5°F (3°C) above dew point.

Preceding coat: According to Neogard Guide Specifications.

Subsequent coat: According to Neogard Guide Specifications.

Product Data Sheet

70750/70751 — Low-Modulus Epoxy
472JB: Base 472J9 : Curing Agent 95YJB



Storage temperature: Store in a cool area to ensure full shelf life. Recommended temperature: 75°F (23°C).

Remarks: Not for use as a topcoat.

Note: **70750/70751 is for professional use only.**

Issued by: Hempel (USA) – 472JB

This Product Data Sheet supersedes those previously issued.

Manufacturer warrants that the physical properties of the product reported above will meet the standards and deviations of the associated ASTM test method. MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. 70750-70751-PDS ksk 03262020.docx

Neogard®, a part of Hempel
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com