

Chemical Resistance Chart

70817/70818 and 70817-01/70818 (57070)

Chemical Resistant Urethane

Rating Key: 0 = No Effect; 1 = Stains/Dulls Film; 2 = Blisters Film; 3 = Lifts Film

Ratings are based on 7-day spot test.

Note: Staining is possible with mustard and urine on white and clear systems.

Chemical	Rating	Chemical	Rating
Acetic Acid (10%)	0	Hydrochloric Acid (5%)	0
Acetic Acid (20%)	0	Hydrochloric Acid (15%)	0-1
Acetic Acid (36%)	0	Hydrofluoric Acid (24%)	0-1
Acetic Acid (98%)	1-2	Hydrochloric Acid (37%)	1
Ammonia (28%)	0	Hydrofluoric Acid (48%)	0-1
Blood	0	Methylisobutyl Ketone	0
Brake Fluid	0-1	Methylpyrrolidione	1-2
Butoxyethanol	0-1	Mineral Spirits	0
Butoxyethylacetate	0-1	Motor Oil	0
Butyl Alcohol	0	Mustard	1
Butylacrylate	0	Nitric Acid (10%)	0-1
Calcium Chloride (10%)	0	Nitric Acid (30%)	0-1
Chromic Acid (2%)	0-1	Oleic Acid	0-1
Citric Acid (25%)	0	Phenol	1
Citric Acid (50%)	0	Phosphoric Acid (25%)	1
Citric Acid (6%)	0	Potassium Hydroxide (25%)	0-1
Citric Acid (70%)	0	Propylene Glycol	0
Diacetone Alcohol	0-1	Skydrol	0
Diesel Fuel	0	Sodium Hydroxide (25%)	0-1
Ethyl Acetate	1	Sodium Hydroxide (50%)	1
Ethyl Alcohol	0	Sodium Hypochlorite (10%)	0-1
Ethylene Glycol	0	Solvent 100	0-1
Formic Acid (38%)	1	Sulfuric Acid (10%)	0-1
Gasoline	0	Sulfuric Acid (50%)	1
Hydrobromic (48%)	1	Sulfuric Acid (96%)	2
Isopropyl Alcohol	0	Tall Oil Fatty Acid	0
Jet Fuel	0	Transmission Oil	0
Ketchup	0	Urine	0
Lactic Acid (20%)	0-1	Vegetable Oil	0
Lactic Acid (50%)	1-2	Vinegar	0
Lactic Acid (85%)	1-2	Xylene	0

Chemical Resistance Chart

70817/70818 and 70817-01/70818 (57070)

Chemical Resistant Urethane



Issued by:	Hempel (USA) – 70817/70718 & 70817-01/70718 (57070)
<p>This Technical Information sheet supersedes those previously issued.</p> <p>Manufacturer warrants that the physical properties of the product reported above will meet the standards and deviations of the associated ASTM test method. MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. 70817-70817-01-70818-CRC ksk 04062020.docx</p> <p>Neogard®, a part of Hempel 2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com</p>	