

# Product Data Sheet

70902/70910 — Floor-Gard/Wall-Gard HD, Satin  
47ZJB: Base 47ZJ9 : Curing Agent 94AJB



**Description:** 70902/70910 (Hempel 47ZJB) is a two-component, water-based, urethane wall and floor coating.

**Recommended use:** As the topcoat for the Neogard Wall-Gard HD wall coating system, and as a topcoat for many Neogard floor coating systems.  
Applications include: hospitals, operating rooms, pharmaceutical manufacturing facilities, clean rooms, schools, food and beverage processing facilities, and various facility wet areas.

**Features:** Low odor and VOC.  
Resists UV.  
Durable; resists scrubbing.

**Availability:** Available in North America. Not included in Group Assortment; other regions must confirm.

## Colors and packaging:

70902-00 (47ZJ900050)	Satin Clear	3-gallon kits (mixed volume)
70910 (94AJB00000)	NA	

*Some standard colors and/or packaging may have extended lead times and/or minimum quantities.*

## Physical constants:

Taber Abrasion, 1,000 cycles CS-17	20 mg loss	ASTM D4060
Pencil Hardness	4H Gouge	ASTM D3363
Volume Solids (mixed)	53.5 %	Calculated
Weight/Gallon (mixed)	9.18 lbs	ASTM D1475
VOC	<10 g/L	ASTM D3960
Shelf Life	1 year	
Dry Time to Touch*	4–6 hours	ASTM D5895
Recoat Time, Tack-Free*	6–24 hours	ASTM D5895
Cure Time*	24 hours	

*\*75°F/23°C, 50% relative humidity. The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at [www.neogard.com](http://www.neogard.com).*

## Application details:

**Version, mixed product** **47ZJB**  
Mixing ratio: Base 47ZJ9 : Curing Agent 94AJB  
2 : 1 by volume

Mixing instructions: Pre-mix base for 3–5 minutes before adding curing agent. Mix for a minimum of 5 minutes before applying. Jiffy Mixer paddle recommended.

Application method: Roller, brush, spray (contact Neogard for spray equipment information)

Thinner (max.vol.): Water (10%)

Pot life: 90 minutes at 75°F/23°C

Recommended film thickness, wet: 4–6 mils

Recommended film thickness, dry: 2–3 mils

Cleaning of tools: Water

**Safety:** Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations.

**Surface preparation:** According to Neogard Guide Specifications.

**Preceding coat:** According to Neogard Guide Specifications.

**Subsequent coat:** According to Neogard Guide Specifications.

# Product Data Sheet

70902/70910 — Floor-Gard/Wall-Gard HD, Satin  
47ZJB: Base 47ZJ9 : Curing Agent 94AJB



**Storage temperature:** Store in a cool area to ensure full shelf life. Recommended temperature: 75°F/23°C. Prevent freezing; product will become unusable if frozen.

**Remarks:** For indoor use only.

**Note:** **70902/70910 is for professional use only.**

**Issued by:** Hempel (USA) – 47ZJB

This Product Data Sheet supersedes those previously issued.

Manufacturer warrants that the physical properties of the product reported above will meet the standards and deviations of the associated ASTM test method. MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. Document9

Neogard®, a part of Hempel  
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com