Product Data Sheet

7261 (387JB) **Acrylic Roof Coating, Quick Set**



Description: 7261 (Hempel 387JB) is a high solids, quick set, elastomeric acrylic coating.

Recommended use: As a protective coating on polyurethane, built-up, modified bitumen, metal, or single-ply roofs.

Features: Fire retardant.

Meets South Coast Air Quality Management District (SCAQMD) VOC requirements.

Certificates/approvals: LEED: MRc5, SSc7.2

CRRC: 0720-0002 UL: TGFU.R6034 Factory Mutual: Class A **Energy Star: Certified**

Availability: Available in North America. Not included in Group Assortment; other regions must confirm.

Colors and packaging:

7261 (387JB10000) White 55- and 5-gallon

Physical constants:

ASTM D2370 Tensile Strength 280 psi Elongation 270% **ASTM D2370** Permanent Set <20% ASTM D412 Water Resistance <20% ASTM D471 MVT at 30 mils 2.9 English perms ASTM E96

Weight/Gallon 11.5 lbs/gal **ASTM D1475** Weight Solids **ASTM D4209** 63% Volume Solids 50% Calculated VOC 38 g/L EPA Method 24 Flash Point None **ASTM D3278** 2 years (unopened container)

Shelf Life Cure Time at 75°F (23°C), 50%

relative humidity

1-2 hours

The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at www.neogard.com.

Application details:

Application method: Roller or spray (contact Neogard for spray equipment information)

Thinner: Not recommended; contact Neogard for more information Mixing: Mix for a minimum of 3-5 minutes before applying

Cleaning of tools: Water

Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels Safety:

on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or

national safety regulations.

Surface preparation: According to Neogard Guide Specifications.

Application conditions: Must be applied at 50°F/10°C or higher. Substrate temperature must be above 40°F/5°C and/or

below 100°F/37°C, and more than 5°F/3°C above the dewpoint and rising. Temperatures must

remain above freezing (32°F/0°C) for 12 hours after application.

Apply only in dry conditions. Do not apply if weather conditions prevent complete cure before rain, dew, or freezing temperatures occur. Do not apply in late afternoon if heavy condensation may

occur overnight. Cool temperatures and high humidity will retard cure.

Issued: July 2020 Page: 1/2

Product Data Sheet

7261 (387JB) Acrylic Roof Coating, Quick Set



Preceding coat: According to Neogard Guide Specifications.

Subsequent coat: According to Neogard Guide Specifications.

Storage temperature: Store in a cool area to ensure full shelf life. Recommended temperature: 75°F/23°C. Prevent

freezing; 7261 will become unusable if frozen.

Remarks: Not designed for use on roofs that have any ponding water. Requires complete evaporation of

water to cure.

Note: 7261 is for professional use only.

Issued by: Hempel (USA) – 387JB

This Product Data Sheet supersedes those previously issued.

Manufacturer warrants that the physical properties of the product reported above will meet the standards and deviations of the associated ASTM test method.

MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY
IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Buyer must make its own determination of
the suitability of any product for its use, whether such product is used alone or in combination with other materials. To the extent this or any of Manufacturer's products is
proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE
LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON
OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS. Nothing contained herein shall be construed to
constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed
as an employee or agent of Manufacturer. 7261-PDS ksk 07062020.docx

Neogard®, a part of Hempel 2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com

Issued: July 2020 Page: 2/2