Product Data Sheet

7470 (47LJB) Aliphatic Urethane



Description: 7470 series (Hempel 47LJB) is a single-component aliphatic urethane.

Recommended use: As a weather protective topcoat for pedestrian and vehicular traffic-bearing waterproofing

systems. Areas include parking garages, stadiums, balconies, plaza decks, pedestrian walkways,

and rooftop recreational areas.

Certificates/approvals: LEED: MRc5, SSc7.1 (7470-011)

Factory Mutual: Class A (7470-002, -011)

Miami-Dade: NOA No.: 15-0421.01 (7470-002, -011)

Availability: Available in North America. Not included in Group Assortment; other regions must confirm.

Colors and packaging:

7470-002 (47LJB16650) Gray 7470-003 (47LJB23820) Tan 7470-011 (47LJB16660) Light Gray

7470-011 (47LJB19000) Eight Gray 5-gallon pail (all versions)

7470-041 (47LJB16680) Charcoal Gray 7470-058 (47LJB61300) Dark Maple

Some standard colors and/or packaging may have extended lead times and/or minimum quantities. Contact

Neogard for additional colors.

Physical constants:

Tensile Strength 2,500 psi ASTM D412 Elongation 250% ASTM D412 Permanent Set <20% ASTM D412 Tear Resistance 400 pli **ASTM D1004** Water Resistance 1%, 7 days ASTM D471 MVT at 20 mils 2.5 English Perm ASTM E96 **Taber Abrasion** 10 mg/1,000 CS-17 **ASTM D4060** Shore A 88-92 **ASTM D2240** Adhesion >400 psi **ASTM D4541** SRI Value: 7470-011 ASTM E1980-01 81

Weight/Gallon 8.95 lbs/gal **ASTM D1475** Weight Solids 81.8% at 12 hours **ASTM D4209** Volume Solids 77.7% Calculated EPA Method 24 VOC 195 g/L Viscosity 84 KŪ **ASTM D2196** Flash Point 110°F/43°C By Comparison

Shelf Life 1 year

Cure to Recoat at 75°F/23°C, 50% 8-12 hours, 72 hours for

relative humidity vehicular traffic

The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further

technical information can be found at www.neogard.com.

Application details:

Application method: Roller or squeegee

Thinner (max.vol.): Hempel's Thinner 08080 (10%)

Mixing: Mix for 3–5 minutes before applying; Jiffy Mixer paddle recommended

Pot life: NA for single-component, unaccelerated urethane

Cleaning of tools: Hempel's Thinner 08080

Issued: March 2020 Page: 1/2

Product Data Sheet

7470 (47LJB) Aliphatic Urethane



Safety: Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels

on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or

national safety regulations.

Application conditions: Substrate temperature must be between 40°F/4°C and 110°F/43°C.

Preceding coat: According to Neogard Guide Specifications.

Accelerators and additives: 7986 (994JB00000): Odor mask, synthetic vanilla scent.

7923 (9505300000): Accelerator for single component urethanes.

7931 (9905500000): Fast accelerator for use in low humidity environments.

Storage temperature: Store in a cool area to ensure full shelf life. Recommended temperature: 75°F/23°C.

Remarks: Not recommended for constant immersion. Not compatible with asphaltic compounds.

For on-grade applications, substrates constructed over unvented metal decks or between-slab

applications, contact Neogard Technical Service.

Note: 7470 is for professional use only.

Issued by: Hempel (USA) – 47LJB

This Product Data Sheet supersedes those previously issued.

Manufacturer warrants that the physical properties of the product reported above will meet the standards and deviations of the associated ASTM test method.

MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY
IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Buyer must make its own determination of
the suitability of any product for its use, whether such product is used alone or in combination with other materials. To the extent this or any of Manufacturer's products is
proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE
LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON
OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS. Nothing contained herein shall be construed to
constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed
as an employee or agent of Manufacturer. 7470-PDS ksk 03262020.docx

Neogard®, a part of Hempel 2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com

Issued: March 2020 Page: 2/2