## **Product Data Sheet**

## 7490-CA (47YJB)

### Aliphatic Urethane Roof Coating, SCAQMD-Compliant



**Description:** 7490-CA (Hempel 47YJB) is a single-component, aliphatic polyurethane.

**Recommended use:** As a weather-protective topcoat for polyurethane foam, concrete, metal, single-ply and built-

up/modified bitumen roof systems.

Features: Meets South Coast Air Quality Management District (SCAQMD) VOC requirements.

Certificates/approvals: LEED: MRc5, SSc7.2

CRRC: 0720-0005

Miami-Dade: NOA No.: 16-0222.02, NOA No.: 16-0322.27

UL: TGFU.R6034

USDA BioPreferred: 21% content

Available in North America. Not included in Group Assortment; other regions must confirm.

#### Colors and packaging:

7490-CA (47YJB10000) White

7490-CA (47YJB16660) Light Gray 5- and 55-gallon

7490-CA (47YJB23820) Tan

#### **Physical constants:**

ASTM D412 Tensile Strength 2,300 psi Elongation 230% ASTM D412 Permanent Set 10% ASTM D412 Tear Resistance 200 pli **ASTM D1004** Water Resistance <2% at 7 days ASTM D471 **Taber Abrasion** 16 mg, 1,000 CS-17 **ASTM D4060** MVT at 20 mils 0.9 perms ASTM E96 Shore A 85 **ASTM D2240** Fire Resistance Pass (as part of a system) ASTM E108

 Weight/Gallon
 10.77 lbs/gal
 ASTM D1475

 Weight Solids
 79.5%
 ASTM D5201

 Volume Solids
 76.7%
 ASTM D5201

 VOC
 <50 g/L</td>
 ASTM D5201

 Viscosity
 100 KU
 ATSM D2169

Cure Time, 77°F/25°C, 50% relative 6-12 hours

humidity

Cure to Recoat, 75°F/23°C, 50%

relative humidity

18 hours minimum

The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at www.neogard.com.

#### **Application details:**

Application method: Roller or spray (contact Neogard for spray equipment information)

Thinner (max.vol.): Acetone (10%)

Mixing: Mix for 3–5 minutes before applying; Jiffy Mixer paddle recommended

Cleaning of tools: Acetone

Safety: Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels

on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or

national safety regulations.

Application conditions: Substrate temperature must be above 40°F/5°C and/or below 100°F/37°C, and more than 5°F/3°C

above the dewpoint and rising.

Issued: May 2020 Page: 1/2

## **Product Data Sheet**

# 7490-CA (47YJB) Aliphatic Urethane Roof Coating, SCAQMD-Compliant



**Preceding coat:** According to Neogard Guide Specifications.

Accelerators and additives: 7986 (994JB00000): Odor mask, synthetic vanilla scent.

7987 (995JB00000): Odor mask, orange scent.

Storage temperature: Store in a cool area to ensure full shelf life. Recommended temperature: 75°F/23°C.

Remarks: Product is sensitive to moisture; not recommended for constant immersion. Concrete must have a

full 28 day cure period prior to coating. Not compatible with asphaltic compounds. Not for use with insulating concrete such as Zonolite, Vermiculite, Perlite, etc. Not for use over aluminized coated

roofs.

Note: **7490-CA is for professional use only.** 

Issued by: Hempel (USA) – 47YJB

This Product Data Sheet supersedes those previously issued.

Manufacturer warrants that the physical properties of the product reported above will meet the standards and deviations of the associated ASTM test method.

MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY
IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Buyer must make its own determination of
the suitability of any product for its use, whether such product is used alone or in combination with other materials. To the extent this or any of Manufacturer's products is
proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE
LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON
OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS. Nothing contained herein shall be construed to
constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed
as an employee or agent of Manufacturer. 7490-CA-PDS ksk 05132020.docx

Neogard®, a part of Hempel 2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com

Issued: May 2020 Page: 2/2