

Product Data Sheet

7740/7741 — Epoxy Primer
252JB: Base 252J9 : Curing Agent 95WJB



Description: 7740/7741 (Hempel 252JB) primer is a two-component, 100% solids epoxy primer.

Recommended use: 7740/7741 primer is applied to wood and concrete surfaces prior to applying surface applied waterproofing systems, in particular Pool-Gard C.

Availability: Available in North America. Not included in Group Assortment; other regions must confirm.

Colors and packaging:

7740 (252J900000)	Brown	3-gallon kit
7741 (95WJB00000)	Neutral	

Physical constants:

Water Resistance	<2%	ASTM D570
MVT @ 10 Mils	<0.11	ASTM E96
Taber Abrasion	53 mg/1,000 cs17	ASTM D4060
Shore D	80	ASTM D2240
Adhesion	650 psi	ASTM D4541
Weight/Gal (mixed)	9.95 lbs/gal	ASTM D1475
Weight Solids (mixed)	99.1%	ASTM D4209
Volume Solids (mixed)	98.6%	Calculated
Viscosity (mixed)	6,000 cps	ASTM D2196
VOC (mixed)	<11 g/L	EPA Method 24

The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at www.neogard.com.

Application details:

Version, mixed product **252JB**
Mixing ratio: Base 252J9 : Curing Agent 95WJB
2 : 1 by volume

Mixing instructions: Pre-mix base for 3–5 minutes before adding curing agent. Mix for a minimum of 5 minutes before applying. Jiffy Mixer paddle recommended.

Application method: Roller or spray (contact Neogard for spray equipment information)

Thinner: Do not thin

Pot life: 60–90 minutes at 75°F (23°C)

Cleaning of tools: HEMPEL'S THINNER 08080 (xylene)

Safety: Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations.

Surface preparation: According to Neogard Guide Specifications.

Application conditions: According to Neogard Guide Specifications.

Subsequent coat: According to Neogard Guide Specifications.

Storage temperature: 50°F–85°F (10°C–30°C)

Remarks: Do not thin 7740/7741.

Product Data Sheet

7740/7741 — Epoxy Primer

252JB: Base 252J9 : Curing Agent 95WJB



Note: **7740/7741 is for professional use only.**

Issued by: Hempel (USA) – 252JB

This Product Data Sheet supersedes those previously issued.

Manufacturer warrants that the physical properties of the product reported above will meet the standards and deviations of the associated ASTM test method. MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. 7740-7741-PDS ksk 03032020.docx

Neogard®, a part of Hempel
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com