Product Data Sheet

NeoQuartz (66GJB) Crystalline Quartz Granules, Broadcast Medium, UV-Stable



Description: NeoQuartz granules are a colored, crystalline quartz, UV-stable flooring and deck coating

aggregate.

Recommended use: As an aggregate for decorative and industrial flooring systems, and decorative deck coating

systems.

Availability: Available in North America. Not included in Group Assortment. Availability subject to confirmation.

Colors and packaging:

66GJB99980 Contact Neogard 50-pound bag (all colors)

Requires a minimum order of 8 bags. Some standard colors and/or packaging may have extended lead times

and/or minimum quantities.

Physical constants:

Hardness (Moh's Scale) 6.5–7

Bulk density 90–100 pounds/cubic foot ASTM C29/C29-97 (2003)

Specific gravity 2.65 ASTM C128-01e1

Composition

MaterialWeight %Silica sand97.5Resin2.65Various colorants0.5

Chemical analysis

 $\begin{array}{lll} \text{SiO}_2 & 99.808\% \\ \text{Fe}_2 & 0.016\% \\ \text{Al}_2\text{O}_3 & 0.042\% \\ \text{CaO \& MgO} & 0.200\% \\ \text{Loss on ignition} & 0.100 \\ \end{array}$

Sieve analysis Retained %

 20
 9.0

 30
 12.4

 40
 54.0

 50
 22.0

 70
 1.9

 100
 0.7

Application details:

Application method: Broadcast; rate according to Neogard system Guide Specifications.

Safety: Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels

on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or

national safety regulations.

Storage temperature: Store in a dry area.

Issued: March 2020 Page: 1/2

Product Data Sheet

NeoQuartz (66GJB) Crystalline Quartz Granules, Broadcast Medium, UV-Stable



Note: **NeoQuartz is for professional use only.**

Issued by: Hempel (USA) – 66GJB

This Product Data Sheet supersedes those previously issued.

Manufacturer warrants that the physical properties of the product reported above will meet the standards and deviations of the associated ASTM test method.

MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY
IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Buyer must make its own determination of
the suitability of any product for its use, whether such product is used alone or in combination with other materials. To the extent this or any of Manufacturer's products is
proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE
LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON
OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS. Nothing contained herein shall be construed to
constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed
as an employee or agent of Manufacturer. NeoQuartz-PDS ksk 03032020.docx

 $Neogard^{\circledcirc}, a part of Hempel \\ 2728 \ Empire \ Central - Dallas, Texas \ 75235 - Phone \ (214) \ 353-1600 - Fax \ (214) \ 357-7532 - www.neogard.com$

Issued: March 2020 Page: 2/2