

# Product Data Sheet

## NeoQuartz (66GJB)

### Crystalline Quartz Granules, Broadcast Medium, UV-Stable



<b>Description:</b>	NeoQuartz granules are a colored, crystalline quartz, UV-stable flooring and deck coating aggregate.
<b>Recommended use:</b>	As an aggregate for decorative and industrial flooring systems, and decorative deck coating systems.
<b>Availability:</b>	Available in North America. Not included in Group Assortment. Availability subject to confirmation.

### Colors and packaging:

66GJB99980	Contact Neogard	50-pound bag (all colors)
	<i>Requires a minimum order of 8 bags. Some standard colors and/or packaging may have extended lead times and/or minimum quantities.</i>	

### Physical constants:

Hardness (Moh's Scale)	6.5–7	
Bulk density	90–100 pounds/cubic foot	ASTM C29/C29-97 (2003)
Specific gravity	2.65	ASTM C128-01e1

### Composition

Material	Weight %
Silica sand	97.5
Resin	2.65
Various colorants	0.5

### Chemical analysis

SiO <sub>2</sub>	99.808%
Fe <sub>2</sub>	0.016%
Al <sub>2</sub> O <sub>3</sub>	0.042%
CaO & MgO	0.200%
Loss on ignition	0.100

### Sieve analysis

	Retained %
20	9.0
30	12.4
40	54.0
50	22.0
70	1.9
100	0.7

### Application details:

Application method: Broadcast; rate according to Neogard system Guide Specifications.

**Safety:** Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations.

**Storage temperature:** Store in a dry area.

# Product Data Sheet

NeoQuartz (66GJB)

Crystalline Quartz Granules, Broadcast Medium, UV-Stable



Note: **NeoQuartz is for professional use only.**

Issued by: Hempel (USA) – 66GJB

This Product Data Sheet supersedes those previously issued.

Manufacturer warrants that the physical properties of the product reported above will meet the standards and deviations of the associated ASTM test method. MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. NeoQuartzUV-PDS ksk 03032020.docx

Neogard®, a part of Hempel  
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - [www.neogard.com](http://www.neogard.com)